

SCONA TSPP 10213 GB

Adhesion promoter to improve the mechanical properties of polypropylene (PP) filler, PP glass fiber, PP carbon fiber, and PP natural fiber compounds as well as one-packs in polypropylene.

Product Data

Composition

Polypropylene (random copolymer) functionalized with maleic acid anhydride (MAH)

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

MVR of the carrier (338 °F, 1.2 kg): 40-100 cm³/10 min

Drying loss (3 h, 230 °F): < 0.9 %

MAH content: > 1.8 %

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Thermoplastics

Special Features and Benefits

SCONA TSPP 10213 GB is a highly effective adhesion promoter for polypropylene compounds with short and long glass fibers, carbon fibers, and fillers (ATH, Mg(OH)₂, CaCO₃) and polypropylene natural fiber compounds – even at a low dosage.

SCONA TSPP 10213 GB improves the mechanical properties of these compounds, especially in polypropylene natural fiber compounds. Here it also reduces water absorption.

Recommended Use

In its supplied form (granulate), the modifier is highly suited to producing one-packs and masterbatches.

Recommended Levels

0.5-2 % additive (as supplied) based on the total formulation, depending on the fiber/filler content.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Good wetting of the fibers/fillers is required for effective compounding. For this reason, the product must be added to the main feed.

SCONA TSPP 10213 GB

Data Sheet
Issue 09/2016



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25®
are registered trademarks of the BYK group.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA