

# CERAFLOUR 913

Micronized polypropylene wax for solvent-borne and aqueous systems, to achieve very fine surface textures. Provides a soft feel effect and matting properties.

## Product Data

### Composition

Micronized polypropylene wax

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density: 0.9 g/ml  
Melting point: 160 °C  
Particle size distribution (laser diffraction, volume distribution): D50: 18 µm D90: 31 µm

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C.

## Applications

### Coatings Industry

#### Special Features and Benefits

CERAFLOUR 913 generates a uniform and easily reproducible texture effect with a very fine surface texture in aqueous and solvent-borne coating systems. It also provides a soft feel effect and is characterized by its outstanding matting properties.

#### Recommended Use

Industrial coatings	■
Coil coatings	■
Wood and furniture coatings	■

■ especially recommended

### Recommended Levels

2-10 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### Incorporation and Processing Instructions

The additive is preferably incorporated at the end of the production process at a moderate shear rate.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45

46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com/additives](http://www.byk.com/additives)

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany