

AQUACER 541

Aqueous emulsion of a montan ester wax for care products and polishes as well as for aqueous coating systems and leather coatings.

Product Data

Composition

Non-ionic montan ester wax emulsion

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (1 h, 257 °F): 30 %
Carrier: Water
Melting point (wax content): 176 °F
Viscosity (73 °F, D=800/s): < 50 mPa·s
pH value (68 °F): 4.5

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C (41 °F) and 35 °C (95 °F). Mix well before use.

Applications

Care Products and Polishes

Special Features and Benefits

AQUACER 541 is used as the main component in aqueous care products and polishes. Mixtures with other wax emulsions (e.g. carnauba wax) to optimize the properties are standard. AQUACER 541 improves surface slip and increases scratch resistance.

Recommended Use

Furniture polish	<input checked="" type="checkbox"/>
Plastic care	<input type="checkbox"/>
Wooden floorboards and cork	<input type="checkbox"/>
Leather care/shoe polish	<input checked="" type="checkbox"/>

☒ especially recommended ☐ recommended

AQUACER 541

Data Sheet
Issue 11/2014

Recommended Levels

3-15 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The wax additive is preferably added after blending the polymers with the plasticizers and water but prior to incorporating surface-active substances, while stirring.

Coatings Industry

Special Features and Benefits

AQUACER 541 improves surface slip and scratch resistance in aqueous coating systems. It also increases the gloss in leather coatings.

Recommended Use

Leather coatings	<input checked="" type="checkbox"/>
Can coatings	<input type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

2-7 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should preferably be post-added using a low shear rate. Mix well before use.



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA