

BYK-025

Silicone-containing defoamer for aqueous high gloss emulsion systems and adhesive systems. Particularly compatible and therefore easy to incorporate.

Product Data

Composition

Solution of foam-destroying polysiloxanes

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.96 g/ml
Non-volatile matter (60 min., 105 °C):	18.5 %
Solvents:	Dipropylene glycol monomethyl ether
Flash point:	76 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur at temperatures below 5 °C. Warm to 20 °C and mix well.

Applications

Coatings Industry

Special Features and Benefits

BYK-025 is recommended for non-pigmented acrylate/polyurethane and polyurethane high gloss emulsion systems. The defoamer is especially recommended for curtain coating application, since it is very easy to incorporate and allows optimizing dosage by post-addition while the paint is running on the curtain coater.

Recommended Levels

0.1-1.5 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be added at any time during production. The amount of defoamer used is often divided (by adding 2/3 into the millbase and 1/3 into the let-down or finished product).

Adhesives

Special Features and Benefits

BYK-025 is a highly compatible defoamer and is specifically recommended for sensitive aqueous adhesive systems.

Recommended Levels

0.05-1 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be added at any time during production. Since the defoamer can be easily incorporated, it allows optimal dosage by post addition.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany