

AQUACER 513

HDPE-based VOC-free wax emulsion for improving the surface protection in aqueous coatings and printing inks as well as in aqueous care products and polishes.

Product Data

Composition

Non-ionic emulsion of an oxidized HD polyethylene wax

VOC-free (< 1500 ppm)

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (60 min., 257 °F): 35 %
Carrier: Water
Melting point (wax content): 275 °F
Viscosity (73 °F, D=800/s): 60 mPa·s
pH value: 9.2

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C / 41 °F and 35 °C / 95 °F. Stir before use.

Applications

Coatings and Printing Inks

Special Features and Benefits

The additive improves the scratch resistance in aqueous coatings. It increases the abrasion resistance in printing inks, as well as the resistance to black heel marking in parquet coatings.

Recommended Use

Architectural coatings	<input checked="" type="checkbox"/>
Wood coatings	<input type="checkbox"/>
Printing inks	<input type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

1-6 % additive (as supplied) based upon total formulation for coatings.

3-14 % additive (as supplied) based upon total formulation for printing inks.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should preferably be post-added using low speed agitation. Stir well before use.

Care Products and Polishes

Special Features and Benefits

AQUACER 513 is compatible with all known polymer dispersions, resin solutions, plasticizers, film-forming agents and surfactants. The wax emulsion exhibits good polishability and dirt repulsion. These characteristics are brought out by blending AQUACER 513 with polymers in a 3:1 ratio (solid wax on solid polymer). A mixing ratio of 1:6 increases the water- and alcohol-resistance, the abrasion resistance, and protection against heel marks (= foot traffic resistance).

Recommended Use

AQUACER 513 is used in self-shine floor care products for all types of floors, e.g., with hard floor surfaces such as stone, granite, and marble, as well as soft floors such as parquet, PVC, linoleum and rubber.

Recommended Levels

5-10 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The wax additive is preferably added with stirring after blending the polymers with the plasticizers and water, although before the incorporation of surface active substances.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra. The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA