

HORDAMER PE 03

Primary polyethylene dispersion for formulating release agents for metal die casting.

Product Data

Composition

Primary polyethylene dispersion with anionic and non-ionic emulsifiers

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

| | |
|------------------------------------|-----------------|
| Density (68 °F): | 8.18 lbs/US gal |
| Non-volatile matter (1 h, 257 °F): | 40 % |
| Carrier: | Water |
| Melting point (wax content): | 203 °F |
| Viscosity (68 °F): | 20 mPa·s |
| pH value (68 °F): | 9 |

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C (41 °F) and 35 °C (95 °F). Mix well before use.

Applications

Release Agents for Metal Die Casting

Special Features and Benefits

HORDAMER PE 03 is recommended for formulating aqueous mold release agents which are used in aluminum die casting. The product brings about a good wetting of the mold at high temperatures, very good film forming and outstanding adhesion to the mold surface. The mold is protected from damage and the finished molded components have an excellent surface quality.

HORDAMER PE 03 also remains stable in hard water.

Recommended Levels

10-70 % additive PE 03 (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

HORDAMER PE 03 is preferably diluted with water, but can also be mixed directly with all the components of the aqueous mold release agent.

HORDAMER PE 03

Data Sheet
Issue 05/2014



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABÉN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.
This issue replaces all previous versions – Printed in the USA