

BYKJET-9150

High molecular weight wetting and dispersing additive for solvent-free UV-curable inkjet inks. Suitable for all pigment types.

Product Data

Composition

Solution of a structured copolymer with pigment-affinic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.


Amine value: 12 mg KOH/g
Acid value: 5 mg KOH/g
Active substance: 70 %
Density (68 °F): 8.94 lbs/US gal
Solvents: Propoxylated neopentyl glycol diacrylate (PONPGDA)

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Store at temperatures below 30 °C (86 °F). Do not expose to direct sunlight.



Applications

Inkjet Inks

Special Features and Benefits

High molecular weight wetting and dispersing additive for solvent-free, UV-curable inkjet inks. The additive improves pigment wetting and, thanks to its outstanding steric stabilization of the pigments, it also improves the optical properties of the systems (color strength, gloss, haze, transparency). The viscosity of the pigment concentrates and the finished inkjet inks is reduced and thixotropy prevented. Long-term stability without viscosity change is achieved. BYKJET-9150 also generates a uniform electrical charge across the pigment particles, thereby preventing possible co-flocculation of particles that are not equally charged. The excellent deflocculation causes a very small particle size and a narrow particle size distribution, which achieves short filtration times.

Recommended Use

BYKJET-9150 is suitable for all solvent-free, UV-curable inkjet inks. It stabilizes the majority of the pigments that are usually used in inkjet inks.

Recommended Levels

40-100 % additive (as supplied) based on organic pigments.

45-120 % additive (as supplied) based on carbon black pigments.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Wetting and dispersing additives should generally be added to the millbase. Only in this way can they be fully effective. Pre-mix the resin and reactive thinner of the millbase and then gradually let the additive flow in whilst stirring. Only add the pigments when the additive has been thoroughly distributed.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25®
are registered trademarks of the BYK group.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA