

OPTIGEL-CMO

Rheology additive based on an activated phyllosilicate for aqueous coating systems to generate thixotropic flow behavior.

Product Data

Composition

Activated phyllosilicate

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Specific density: 2.6 g/cm³
Bulk density: 500-700 kg/m³
Moisture content: max. 13 %
Supplied as: free-flowing, cream-colored powder
pH value (2 % in H₂O): 10-11

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

OPTIGEL-CMO is hygroscopic and should be transported and stored dry in the unopened original container at temperatures between 0 °C and 30 °C.

Applications

Coatings Industry

Special Features and Benefits

OPTIGEL-CMO generates thixotropic flow behavior. It improves processability and storage stability as it is highly effective at preventing solids settling. In addition, it reduces the sagging tendency after application which makes it possible to achieve greater layer thicknesses. OPTIGEL-CMO is inorganic and stable to diluted acids and bases.

Recommended Use

OPTIGEL-CMO is suitable for a variety of aqueous coating systems and particularly suitable for use in architectural coatings.

Architectural coatings	<input checked="" type="checkbox"/>
------------------------	-------------------------------------

☒ especially recommended ☐ recommended

Recommended Levels

0.1-3.0 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

OPTIGEL-CMO is hydrophilic and easy to incorporate in water. To ensure optimum distribution and the best possible effectiveness and reproducibility in applications, the additive must be added to water (20 °C ± 5 °C) slowly whilst stirring, and pre-dispersed at high shear forces for at least 20 minutes. OPTIGEL-CMO should be fully hydrated before the remaining formulation components can be added to the dispersion. No wetting or dispersing additives are required to produce this dispersion. Ionic substances with potassium, calcium, magnesium or ammonium ions or acids should be added only after the additive has been fully dispersed.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany