

CERAFLOUR 917

Temperature stable wax additive with excellent shear stability for solvent-borne and aqueous coating systems.

Product Data

Composition

Micronized, organic polymer

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Appearance: White powder
Melting point: 275 °F
Particle size distribution (laser diffraction, volume distribution): D50: 42 µm D90: 64 µm µm

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C (122 °F).

Applications

Coatings Industry

Special Features and Benefits

This additive makes it possible to achieve homogeneous and even surface textures. It is characterized by a high shear stability and is also suitable for roller applications, which reach very high shear forces during application. As a result of the high melt viscosity of the wax, the wax particles do not change shape, even at high baking temperatures. In spray coatings, a soft touch effect can be achieved. The wax increases the scratch and abrasion resistance of coatings.

CERAFLOUR 917

Data Sheet
Issue 08/2013

Recommended Use

Coil coatings	<input checked="" type="checkbox"/>
Industrial coatings	<input checked="" type="checkbox"/>
Wood coatings	<input type="checkbox"/>

☒ especially recommended ☐ recommended

For solvent-borne and aqueous baking systems, two-pack and air-drying systems.

Recommended Levels

1-6 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be added at the end of the production process and should be incorporated at a moderate shear rate.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.
This issue replaces all previous versions – Printed in the USA