

BYK-1162

Highly effective, plasticizer-free dispersing medium for solid dispersions for use in PVC plastisols. Particularly suited to organic pigments and carbon blacks.

Product Data

Composition

Kombination oberflächenaktiver Substanzen

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value:	4 mg KOH/g
Density (68 °F):	7.43 lbs/US gal
Refractive index (68 °F):	1.460
Non-volatile matter (10 min., 302 °F):	95 %
Flash point:	> 284 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur at temperatures below 0 °C (32 °F). Warm to 20 °C (68 °F) and mix well. Do not exceed 50 °C (122 °F).

Applications

PVC Plastisols

Special Features and Benefits

The plasticizer-free dispersing medium BYK-1162 contains multi-functional deflocculating groups for wetting and stabilizing carbon blacks and organic pigments. The achievable concentration of solids for organic pigments is between 20-40 % and for carbon blacks between 15-35 %. The formulation of the solid dispersions with BYK-1162 presents the following advantages compared with standard systems:

- Greater concentration of solids with lower agglomeration
- Narrower particle size distribution
- Free from plasticizers
- Cost savings

Incorporation and Processing Instructions

The solids are incorporated directly into the dispersing medium.

Special Note

- An additional additivation with wetting and dispersing additives is possible at any time.
- If sedimentation or separation occurs in the formulation, this can generally be avoided by adding 0.2-1 % of BYK-410.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.
This issue replaces all previous versions – Printed in the USA