

# CERAFLOUR 925

Finely micronized wax additive for aqueous and solvent-borne systems for increasing slip with simultaneous improvement of scratch resistance.

## Product Data

### Composition

Micronized, modified polyethylene wax

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Particle size distribution D50: 6 µm

Particle size distribution D90: 10 µm

Melting point: 239 °F

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C (122 °F).

## Applications

### Coatings Industry

#### Special Features and Benefits

In can coatings and coil coatings, CERAFLOUR 925 offers a good balance of scratch resistance and surface slip. Within this, the additive has no negative influences on other coating properties such as substrate wetting, intercoat adhesion or compound adhesion.

In solvent-borne coatings, CERAFLOUR 925 increases abrasion resistance. The additive has no negative influences on other coating properties.





CERAFLOUR 925 improves abrasion and scratch resistance in solvent-borne and water-borne wood coatings as well as UV-overprint varnishes. Possible areas of application include decorative furniture foils.

CERAFLOUR 925 can also be used in aqueous systems which contain a high proportion of organic co-solvents. The additive is suitable for high-gloss systems and can also be used in thin layers.

## CERAFLOUR 925

Data Sheet  
Issue 10/2013

### Recommended Use

Can Coatings	
Coil Coatings	
Wood Coatings	
Industrial Coatings	

 particularly recommended    recommended

### Recommended Levels

0.3-2.0 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal dosage levels are determined through a series of tests.

### Incorporation and Processing Instructions

The additive can be incorporated at any time during paint production with moderate shear forces.

### Leather Finishes

#### Special Features and Benefits

CERAFLOUR 925 improves the haptic of solvent-containing and aqueous leather finishes. The additive can be used for matting.

#### Recommended Levels

1-6 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal dosage levels are determined through a series of tests.

#### Incorporation and Processing Instructions

The additive can be incorporated at any time during paint production with moderate shear forces.



Additive Guide



**BYK USA Inc.**  
524 South Cherry Street  
P.O. Box 5670  
Wallingford, CT 06492  
USA  
Tel 203 265-2086  
Fax 203 284-9158

[cs.usa@byk.com](mailto:cs.usa@byk.com)  
[www.byk.com/additives](http://www.byk.com/additives)

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA