

# BYK-1798

Silicone-containing defoamer for aqueous and radiation-curable systems.

## Product Data

### Composition

Solution of a modified polysiloxane copolymer

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.88 g/ml
Non-volatile matter (10 min., 150 °C):	10 %
Solvents:	Butylglycol/ethylhexanol/white spirit 6/2/1
Flash point:	53 °C

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Special Note

The additive contains C<sub>6</sub>F<sub>13</sub> fluorotelomers. It replaces BYK-020.

## Applications

### Coatings and Printing Inks

#### Special Features and Benefits

BYK-1798 is a very effective silicone defoamer for all water-soluble systems (physically drying and baking systems) and is also recommended for radiation-curable coatings.

#### Recommended Levels

0.1-0.7 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

#### Incorporation and Processing Instructions

To ensure the full effect, the defoamer should be added already during the grinding. If post-adding, ensure a sufficiently high shear force in order to distribute the additive well and to prevent cratering.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

**info@byk.com**  
**www.byk.com**

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany