

BYK-C 8002

Reactive, polymeric coupling agent to improve mechanical properties in ATH-filled acrylate systems. It also improves the anti-settling properties.

Product Data

Composition

Solution of a reactive copolymer with filler-affinic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F): 8.60 lbs/US gal

Refraction index: 1.431

Non-volatile matter (20 min, 221 °F): 30 %

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

To be stored and transported at a temperature below 40 °C (104 °F).

Applications

Ambient Curing Resin Systems

Special Features and Benefits

BYK-C 8002 increases the mechanical properties such as flexural strength, compressive strength and the E modulus by up to 30 %. The additive also improves the anti-settling properties of the formulation.

It is recommended for acrylate resins (PMMA in MMA), which are filled with amphoteric or basic fillers such as ATH (aluminium trihydroxide). In the tested formulations, the additive showed no negative impact on hot water and weather resistance.

Recommended Levels

0.1-0.5 % additive (as supplied) based upon the filler.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be added to the resin at any stage of the production process whilst stirring.

BYK-C 8002

Data Sheet
Issue 07/2015



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABÉN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.
This issue replaces all previous versions – Printed in the USA