

Digital Material Passport

Manufacturer		Customer	Business Transaction	
ACME Metal Works GmbH Industrial Park 123 52066 Aachen DE quality@acme-metal.example.com		Global Steel Trading Ltd. Commerce Way 789 2000 Antwerp BE orders@globalsteel.example.com	Order	PO-65478 · 75000 kg Pos. 1-10 · 2025-04-15
Goods Receiver Global Steel Trading Ltd. - Rotterdam Warehouse Harbor District 45 Pier 7 3089 Rotterdam NL			Delivery	DN-98761 · 75000 kg Pos. All · 2025-05-17

Product

Product Name	Structural Steel S355J2+N - Various Shapes	Name (EN)	1.0577
Batch ID	H-79513-03	Marking	S355J2+N laser marked on web surface with clear legibility.
Surface Condition	Hot-rolled	Packaging	Crated bundles of 10 pieces with steel straps in good condition.
Weight	75000 kg	Product Norm	EN 10025-2 (2019)
Production Date	2025-05-16	HS Code	721633 - H sections of iron or non-alloy steel
Country of Origin	DE	CN8 (EU)	72163300 - H-sections of iron or non-alloy steel
Specification	1180-1/ ISO GENERIC - HR - Rev 2024-11-07	HTS (US)	7216330000 - H-sections of iron or nonalloy steel

Chemical Analysis

Heat Number **H-79513** - Melting Process **BOF+LF** - Casting Method **ContinuousCasting** - Casting Date **2025-05-15** - Sample Location **Ladle**

Symbol	C	Mn	Si	P	S	CEV
Unit	%	%	%	%	%	%
Min						
Max	0.20	1.60	0.50	0.025	0.020	0.45
Actual	0.17	1.47	0.25	0.017	0.011	0.42

CEV = C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15: 0.42%

Mechanical Properties

Tensile Strength ¹	Symbol	1	2	3	Average	Min	Max	Spec Min	Spec Max	Method
Value [MPa]	Rm	523	525	527	525	523	527	470	630	EN ISO 6892-1
Yield Strength ¹	Symbol	1	2	3	Average	Min	Max	Spec Min	Spec Max	Method
Value [MPa]	ReH	383	385	387	385	383	387	355	630	EN ISO 6892-1
Elongation after fracture ¹	Symbol	1	2	3	Average	Min	Max	Spec Min	Spec Max	Method
Value [%]	A	22.5	23	23.5	23	22.5	23.5	20	630	EN ISO 6892-1
Impact test ISO-V at -20°C (transverse HEAD) - informative 3 specimens tested at -20°C	Symbol	1	2	3	Average	Min	Max	Std Dev	Spec Min	Method
Value [J]	KV	40	42	44	42	40	44	2	27	EN ISO 148-1

¹ 3 specimens tested

Validation

We hereby certify that all material described above has been manufactured and tested in accordance with the requirements of EN 10025-2:2019 and EN 10204:2004 type 3.1. The results comply with the requirements for S355J2+N steel grade.

Validated by **Klaus Müller**, Quality Control Manager,
Quality Assurance - 2025-05-18