

Manufacturer / Hersteller	Customer / Kunde	Business Transaction / Geschäftsvorgang	
ACME Metal Works GmbH Industrial Park 123 52066 Aachen DE quality@acme-metal.example.com	Engineering Solutions Ltd. Tech Park Way 45 Cardiff CF14 5DU GB procurement@engisolutions.example.com	Order / Bestellung	PO-78901 · 5000 kg Pos. 10 · 2025-04-20
		Delivery / Lieferung	DN-56789 · 5000 kg Pos. 1 · 2025-05-12

Product / Produkt

Product Name / Produktname	Structural Steel S355J2	Name (EN)	1.0577
Batch ID / Chargen-ID	H-10987-02	Shape / Form	RoundBar - D 50 mm - Length 6000 mm
Surface Condition / Oberflächenzustand	Hot-rolled	Packaging / Verpackung	Hexagonal bundles of 5 pieces with wire binding in good condition.
Weight / Gewicht	5000 kg	Product Norm / Produktnorm	EN 10025-2 (2019)
Production Date / Produktionsdatum	2025-05-09	HS Code / HS-Code	720839 - Flat-rolled products of iron or non-alloy steel, of a width of 600 mm or more, hot-rolled, not clad, plated or coated
Country of Origin / Ursprungsland	DE	CN8 (EU)	72083900 - Flat-rolled products of iron or non-alloy steel, of a width of 600 mm or more, hot-rolled, not clad, plated or coated, of a thickness of 4.75 mm or more
Specification / Spezifikation	EN 10025-2 - Rev 2019 - 2019-11-01		

Heat Treatment / Wärmebehandlung

Process / Prozess: Normalizing - Lot / Los: HT-2024-11-15-B47 - Furnace / Ofen: FURNACE-03 - Date / Datum: 2024-11-15				
Stage / Stufe	Temperature / Temperatur	Duration / Dauer	Cooling / Abkühlen	Atmosphere / Atmosphäre
Austenitizing	920 C			

Chemical Analysis / Chemische Analyse

Heat Number / Schmelznummer H-10987 - Melting Process / Schmelzverfahren EAF+LF - Casting Method / Gießverfahren ContinuousCasting - Casting Date / Gießdatum 2025-05-08 - Sample Location / Probenort Ladle

Symbol	C	Mn	Si	P	S	N	CEV
Unit / Einheit	%	%	%	%	%	%	%
Min							
Max	0.20	1.60	0.50	0.025	0.020	0.009	0.45
Actual / Ist-Wert	0.18	1.45	0.25	0.018	0.012	0.006	0.42

CEV = C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15: 0.42%

Mechanical Properties / Mechanische Eigenschaften

Tensile Strength ¹	Symbol	1	2	3	Average / Durchschnitt	Min	Max	Spec Min / Spez. Min	Spec Max / Spez. Max	Method / Methode
Value / Wert [MPa]	Rm	508	510	512	510	508	512	470	630	EN ISO 6892-1
Yield Strength ¹	Symbol	1	2	3	Average / Durchschnitt	Min	Max	Spec Min / Spez. Min	Spec Max / Spez. Max	Method / Methode
Value / Wert [MPa]	ReH	378	380	382	380	378	382	355	630	EN ISO 6892-1
Elongation after fracture ¹	Symbol	1	2	3	Average / Durchschnitt	Min	Max	Std Dev / Std.-Abw.	Spec Min / Spez. Min	Method / Methode
Value / Wert [%]	A	21.5	22	22.5	22	21.5	22.5	0.5	20	EN ISO 6892-1

¹ 3 specimens tested

Validation / Validierung

We hereby certify that the material described above has been manufactured and tested in accordance with the requirements of EN 10204:2004 type 3.1 and the specified standards. The results comply with the requirements.

Validated by / Validiert von Johann Weber, Quality Inspector, Quality Assurance - 2025-05-14