

Manufacturer / Hersteller	Customer / Kunde	Business Transaction / Geschäftsvorgang	
ThyssenKrupp Steel Europe AG Kaiser-Wilhelm-Straße 100 47166 Duisburg DE quality@thyssenkrupp-steel.example.com	Heavy Industries Construction AB Industrivägen 25 Göteborg 41705 SE procurement@heavy-ind.example.se	Order / Bestellung	PO-2025-1547 · 24800 kg Pos. 10 · 2025-04-10
		Delivery / Lieferung	DN-2025-8854 · 24800 kg Pos. 10 · 2025-05-20

Product / Produkt

Product Name / Produktname	Hot-rolled structural steel plate S355J2+N	Number / Nummer (EN)	1.0577
Batch ID / Chargen-ID	H-58742-12	Name (Material)	S355J2+N
Surface Condition / Oberflächenzustand	Hot-rolled	Shape / Form	Plate - Width 2000 mm - Thickness 25 mm - Length 4500 mm
Delivery Condition / Lieferzustand	+N - Normalized	Product Norm / Produktnorm	EN 10025-2 (2019)
Weight / Gewicht	24800 kg	Product Norm / Produktnorm	EN 10029 (2010)
Production Date / Produktionsdatum	2025-05-18		
Country of Origin / Ursprungsland	DE		
Tolerance Standard / Toleranznorm	EN 10029:2010		

Chemical Analysis / Chemische Analyse

Heat Number / Schmelznummer H-58742 - Melting Process / Schmelzverfahren BOF+LF - Casting Method / Gießverfahren ContinuousCasting - Casting Date / Gießdatum 2025-05-17 - Sample Location / Probenort Ladle

Symbol	C	Mn	Si	P	S
Unit / Einheit	%	%	%	%	%
Min					
Max	0.20	1.60	0.50	0.025	0.020
Actual / Ist-Wert	0.18	1.52	0.28	0.015	0.009

Mechanical Properties / Mechanische Eigenschaften

Property / Eigenschaft	Symbol	Actual / Ist-Wert	Minimum	Maximum	Method / Methode
Tensile Strength ¹	Rm	515 MPa	470 MPa	630 MPa	EN ISO 6892-1
Yield Strength ¹	ReH	378 MPa	355 MPa		EN ISO 6892-1
Elongation after fracture At room temperature, L0=5.65√S0	A	24 %	20 %		EN ISO 6892-1
Charpy V-notch Impact Energy At -20°C, longitudinal	KV	45 J	27 J		EN ISO 148-1

¹ At room temperature

Supplementary Tests / Ergänzende Tests

Test / Prüfung	Result / limits / Ergebnis mit Grenzwerten	Method / Methode	Status
Thickness Measured at 4 points	24.8 mm - min 24.7 mm - max 26.3 mm	EN 10029	✓
Flatness Deviation Measuring length 2000mm, Steel type L	7 mm - max 10 mm	EN 10029	✓
Edge Camber Measured over full length	8.00 mm - max 11.25 mm	EN 10029	✓
Out-of-Squareness Measured at corners	15 mm - max 20 mm	EN 10029	✓

Validation / Validierung

We hereby certify that all material described above has been manufactured and tested in accordance with the requirements of EN 10025-2:2019, EN 10029:2010, and EN 10204:2004 type 3.1. The results comply with the requirements for S355J2+N steel grade and dimensional tolerances class B-S-G.

Validated by / Validiert von Dr. Werner Schmidt, Head of Quality Control, Quality Assurance - 2025-05-20