

Manufacturer / Hersteller	Customer / Kunde	Business Transaction / Geschäftsvorgang	
ACME Metal Works GmbH Industrial Park 123 52066 Aachen DE quality@acme-metal.example.com	Global Steel Trading Ltd. Commerce Way 789 2000 Antwerp BE orders@globalsteel.example.com	Order / Bestellung	PO-65478 · 75000 kg Pos. 1-10 · 2025-04-15
		Delivery / Lieferung	DN-98761 · 75000 kg Pos. All · 2025-05-17 Internal Order ID / Interne Bestellnummer: SO-87432
Goods Receiver / Warenempfänger Global Steel Trading Ltd. - Rotterdam Warehouse Harbor District 45 Pier 7 3089 Rotterdam NL			

Product / Produkt

Product Name / Produktname	Structural Steel S355J2+N - Various Shapes	Name (EN)	1.0577
Batch ID / Chargen-ID	H-79513-03	Marking / Kennzeichnung	S355J2+N laser marked on web surface with clear legibility.
Surface Condition / Oberflächenzustand	Hot-rolled	Packaging / Verpackung	Crated bundles of 10 pieces with steel straps in good condition.
Weight / Gewicht	75000 kg	Product Norm / Produktnorm	EN 10025-2 (2019)
Production Date / Produktionsdatum	2025-05-16	HS Code / HS-Code	721633 - H sections of iron or non-alloy steel
Country of Origin / Ursprungsland	DE	CN8 (EU)	72163300 - H-sections of iron or non-alloy steel
Specification / Spezifikation	1180-1/ ISO GENERIC - HR - Rev 2024-11-07	HTS (US)	7216330000 - H-sections of iron or nonalloy steel

Chemical Analysis / Chemische Analyse

Heat Number / Schmelznummer H-79513 - Melting Process / Schmelzverfahren BOF+LF - Casting Method / Gießverfahren ContinuousCasting - Casting Date / Gießdatum 2025-05-15 - Sample Location / Probenort Ladle

Symbol	C	Mn	Si	P	S	CEV
Unit / Einheit	%	%	%	%	%	%
Min						
Max	0.20	1.60	0.50	0.025	0.020	0.45
Actual / Ist-Wert	0.17	1.47	0.25	0.017	0.011	0.42

CEV = C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15: 0.42%

Mechanical Properties / Mechanische Eigenschaften

Tensile Strength ¹	Symbol	1	2	3	Average / Durchschnitt	Min	Max	Spec Min / Spez. Min	Spec Max / Spez. Max	Method / Methode
Value / Wert [MPa]	Rm	523	525	527	525	523	527	470	630	EN ISO 6892-1
Yield Strength ¹	Symbol	1	2	3	Average / Durchschnitt	Min	Max	Spec Min / Spez. Min	Method / Methode	
Value / Wert [MPa]	ReH	383	385	387	385	383	387	355	EN ISO 6892-1	
Elongation after fracture ¹	Symbol	1	2	3	Average / Durchschnitt	Min	Max	Spec Min / Spez. Min	Method / Methode	
Value / Wert [%]	A	22.5	23	23.5	23	22.5	23.5	20	EN ISO 6892-1	
Impact test ISO-V at -20°C (transverse HEAD) - informative 3 specimens tested at -20°C	Symbol	1	2	3	Average / Durchschnitt	Min	Max	Std Dev / Std.-Abw.	Spec Min / Spez. Min	Method / Methode
	Value / Wert [J]	KV	40	42	44	42	40	44	2	27



ACME METALS

Digital Material Passport / Digitaler Materialpass

ID **DMP-METAL-WRAP-001** - Version **1.0.0**
Issue Date / Ausstellungsdatum **2025-05-18** - Certificate Type / Zertifikatstyp **EN 10204 3.1**

¹ 3 specimens tested

Validation / Validierung

We hereby certify that all material described above has been manufactured and tested in accordance with the requirements of EN 10025-2:2019 and EN 10204:2004 type 3.1. The results comply with the requirements for S355J2+N steel grade.

Validated by / Validiert von **Klaus Müller**, Quality Control Manager, Quality Assurance - 2025-05-18