

Digital Material Passport

Manufacturer	Customer	Business Transaction
ACME Metal Works GmbH Industrial Park 123 52066Aachen DE quality@acme-metal.example.com	Global Steel Trading Ltd. Commerce Way 789 2000Antwerp BE orders@globalsteel.example.com	Order ID PO-65478 - Pos. 1-10 - 2025-04-15 - Quantity 75000 kg Delivery ID DN-98761 - Pos. All - 2025-05-17 - Quantity 75000 kg
Goods Receiver Global Steel Trading Ltd. - Rotterdam Warehouse Harbor District 45 Pier 7 3089Rotterdam NL		

Product

Product Name	Structural Steel S355J2+N - Various Shapes	Name (EN)	1.0577
Batch ID	H-79513-03	Marking	S355J2+N laser marked on web surface with clear legibility.
Surface Condition	Hot-rolled	Packaging	Crated bundles of 10 pieces with steel straps in good condition.
Weight	75000 kg	Product Norm	EN 10025-2 (2019)
Production Date	2025-05-16	HS Code	721633 - H sections of iron or non-alloy steel
Country of Origin	DE	CN8 (EU)	72163300 - H-sections of iron or non-alloy steel
Specification	1180-1/ ISO GENERIC - HR - Rev 2024-11-07	HTS (US)	7216330000 - H-sections of iron or nonalloy steel

Chemical Analysis

Heat Number H-79513 - Melting Process BOF+LF - Casting Method ContinuousCasting - Casting Date 2025-05-15 - Sample Location Ladle									
Symbol	Unit	Min	Max	Actual	Symbol	Unit	Min	Max	Actual
C	%		0.2	0.17	P	%		0.025	0.017
Mn	%		1.6	1.47	S	%		0.02	0.011
Si	%		0.5	0.25	CEV	%		0.45	0.42
CEV = C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15: 0.42%									

Mechanical Properties

Property	Symbol	Actual	Minimum	Maximum	Method
Tensile Strength ¹	Rm	523 / 525 / 527 MPa - Mean 525 - Min 523 - Max 527	470 MPa	630 MPa	EN ISO 6892-1
Yield Strength ¹	ReH	383 / 385 / 387 MPa - Mean 385 - Min 383 - Max 387	355 MPa		EN ISO 6892-1
Elongation after fracture ¹	A	22.5 / 23 / 23.5 % - Mean 23 - Min 22.5 - Max 23.5	20 %		EN ISO 6892-1
Charpy V-notch Impact Energy 3 specimens tested at -20°C	KV	40 / 42 / 44 J - Mean 42 - Min 40 - Max 44 - Std Dev 2	27 J		EN ISO 148-1

¹ 3 specimens tested

Validation

We hereby certify that all material described above has been manufactured and tested in accordance with the requirements of EN 10025-2:2019 and EN 10204:2004 type 3.1. The results comply with the requirements for S355J2+N steel grade.

Validated by **Klaus Müller**, Quality Control Manager,
Quality Assurance - 2025-05-18