

Digital Material Passport

ID DMP-METAL-EN10029-001 - Version 1.0.0
Issue Date 2025-05-20 - Certificate Type EN 10204 3.1

Manufacturer	Customer	Business Transaction
ThyssenKrupp Steel Europe AG Kaiser-Wilhelm-Straße 100 47166 Duisburg DE quality@thyssenkrupp-steel.example.com	Heavy Industries Construction AB Industrivägen 25 Göteborg 41705 SE procurement@heavy-ind.example.se	Order ID PO-2025-1547 - Pos. 10 - 2025-04-10 - Quantity 24800 kg Delivery ID DN-2025-8854 - Pos. 10 - 2025-05-20 - Quantity 24800 kg

Product

Product Name	Hot-rolled structural steel plate S355J2+N	Number (EN)	1.0577
Batch ID	H-58742-12	Name (Material)	S355J2+N
Surface Condition	Hot-rolled	Shape	Plate - Width 2000 mm - Thickness 25 mm - Length 4500 mm
Delivery Condition	+N - Normalized	Product Norm	EN 10025-2 (2019)
Weight	24800 kg	Product Norm	EN 10029 (2010)
Production Date	2025-05-18		
Country of Origin	DE		
Tolerance Standard	EN 10029:2010		

Chemical Analysis

Heat Number **H-58742** - Melting Process **BOF+LF** - Casting Method **ContinuousCasting** - Casting Date **2025-05-17** - Sample Location **Ladle**

Symbol	Unit	Min	Max	Actual	Symbol	Unit	Min	Max	Actual
C	%		0.2	0.18	P	%		0.025	0.015
Mn	%		1.6	1.52	S	%		0.02	0.009
Si	%		0.5	0.28					

Mechanical Properties

Property	Symbol	Actual	Minimum	Maximum	Method
Tensile Strength¹	Rm	515 MPa	470 MPa	630 MPa	EN ISO 6892-1
Yield Strength¹	ReH	378 MPa	355 MPa		EN ISO 6892-1
Elongation after fracture At room temperature, L0=5.65√S0	A	24 %	20 %		EN ISO 6892-1
Charpy V-notch Impact Energy At -20°C, longitudinal	KV	45 J	27 J		EN ISO 148-1

¹ At room temperature

Supplementary Tests

Test	Result / limits	Method	Status
Thickness Measured at 4 points	24.8 mm - min 24.7 mm - max 26.3 mm	EN 10029	✓
Flatness Deviation Measuring length 2000mm, Steel type L	7 mm - max 10 mm	EN 10029	✓
Edge Camber Measured over full length	8 mm - max 11.25 mm	EN 10029	✓
Out-of-Squareness Measured at corners	15 mm - max 20 mm	EN 10029	✓

Validation

We hereby certify that all material described above has been manufactured and tested in accordance with the requirements of EN 10025-2:2019, EN 10029:2010, and EN 10204:2004 type 3.1. The results comply with the requirements for S355J2+N steel grade and dimensional tolerances class B-S-G.

Validated by **Dr. Werner Schmidt**, Head of Quality Control, Quality Assurance - 2025-05-20