

Manufacturer	Customer	Business Transaction	
ACME Metal Works GmbH Industrial Park 123 52066 Aachen DE quality@acme-metal.example.com	Engineering Solutions Ltd. Tech Park Way 45 Cardiff CF14 5DU GB procurement@engisolutions.example.com	Order	PO-78901 · 5000 kg Pos. 10 · 2025-04-20
		Delivery	DN-56789 · 5000 kg Pos. 1 · 2025-05-12

Product			
Product Name	Structural Steel S355J2	Name (EN)	1.0577
Batch ID	H-10987-02	Shape	RoundBar - D 50 mm - Length 6000 mm
Strand ID	3	Packaging	Hexagonal bundles of 5 pieces with wire binding in good condition.
Billet Number	B-4471-01	Product Norm	EN 10025-2 (2019)
Billet Number	B-4471-02		720839 - Flat-rolled products of iron or non-alloy steel, of a width of 600 mm or more, hot-rolled, not clad, plated or coated
Bundle Number	BDL-118	HS Code	72083900 - Flat-rolled products of iron or non-alloy steel, of a width of 600 mm or more, hot-rolled, not clad, plated or coated, of a thickness of 4.75 mm or more
Surface Condition	Hot-rolled	CN8 (EU)	
Weight	5000 kg		
Production Date	2025-05-09		
Country of Origin	DE		
Country of Melt and Pour	CN		
Specification	EN 10025-2 - Rev 2019 - 2019-11-01		

Heat Treatment				
Process: Normalizing - Lot: HT-2024-11-15-B47 - Furnace: FURNACE-03 - Date: 2024-11-15				
Stage	Temperature	Duration	Cooling	Atmosphere
Austenitizing	920 C			

Chemical Analysis							
Heat Number H-10987 - Melting Process EAF+LF - Casting Method ContinuousCasting - Casting Date 2025-05-08 - Sample Location Ladle							
Symbol	C	Mn	Si	P	S	N	CEV
Unit	%	%	%	%	%	%	%
Min							
Max	0.20	1.60	0.50	0.025	0.020	0.009	0.45
Actual	0.18	1.45	0.25	0.018	0.012	0.006	0.42
Piece analysis: C = 0.19% (max. 0.22%), Mn = 1.48% (max. 1.70%)							
CEV = C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15: 0.42%							

Mechanical Properties										
Tensile Strength ¹	Symbol	1	2	3	Average	Min	Max	Spec Min	Spec Max	Method
Value [MPa]	Rm	508	510	512	510	508	512	470	630	EN ISO 6892-1
Yield Strength ¹	Symbol	1	2	3	Average	Min	Max	Spec Min	Method	
Value [MPa]	ReH	378	380	382	380	378	382	355	EN ISO 6892-1	
Elongation after fracture ¹	Symbol	1	2	3	Average	Min	Max	Std Dev	Spec Min	Method
Value [%]	A	21.5	22	22.5	22	21.5	22.5	0.5	20	EN ISO 6892-1

¹ 3 specimens tested

Validation
We hereby certify that the material described above has been manufactured and tested in accordance with the requirements of EN 10204:2004 type 3.1 and the specified standards. The results comply with the requirements.
Validated by Johann Weber, Quality Inspector, Quality Assurance - 2025-05-14