

Manufacturer	Customer	Business Transaction	
Steel Testing Labs GmbH 123 Test Street 10115 Berlin DE	Customer Industries Inc 456 Customer Ave New York 12345 US	Order	ORD-2025-001
		Delivery	DEL-2025-001 · 1000 kg

Product			
Product Name	High Strength Steel Plate	Shape	Plate - Width 2000 mm - Thickness 50 mm - Length 6000 mm
Batch ID	BATCH-2025-001		

Chemical Analysis			
Heat Number H123456 - Melting Process EAF+LF - Casting Method ContinuousCasting - Casting Date 2025-09-28			

Symbol	C	Mn	Si	P	S	Cr	Ni	Mo	Cu	Al	N	CEV
Unit	%	%	%	%	%	%	%	%	%	%	%	%
Min		1.40								0.020		
Max	0.20	1.70	0.50	0.025	0.015	0.30	0.20	0.10	0.25	0.050	0.012	0.45
Actual	0.18	1.45	0.35	0.012	0.008	0.25	0.15	0.08	0.18	0.025	0.008	0.42

CEV = C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15: 0.42%

Mechanical Properties								
Property		Symbol	Actual	Minimum	Maximum	Method	Status	
Tensile Strength¹ Specimen: 1/4T, L		Rm	485 MPa	450 MPa	600 MPa	ASTM E8	✓	
						ASTM E23	✓	
Charpy V-Notch Impact Temperature: -40°C Specimen: 1/4T, L-T								
No.	1	2	3	Average	Min	Max	Std Dev	Spec Min
Value [J]	48	52	45	48.3	45	52	3.5	40

Through-Thickness Tensile					EN 10164	✓
Room temperature, through-thickness direction						
Location (position)	0	0.25	0.5	0.75	1	
Value [MPa]	475	485	490	487	478	

Yield Strength ¹	Re	355 MPa	335 MPa	ASTM E8	✓
Specimen: Surface, T - ID: YS-SURF-T-001					
Elongation ¹	A	22 %	20 %	ASTM E8	✓
Specimen: Custom (Mid-radius at end section), C - ID: ELONG-MR-001					

¹ Room temperature

Validation	
We certify that the material described herein has been tested and inspected in accordance with the specified standards and meets all requirements.	Validated by Dr. Hans Schmidt, Quality Manager - 2025-09-29