

Thermal Stability Limits of Fe-Ni Alloys for Space Applications

Laasya Priya Potharaju, Matilde Barros, Prajwal Basavaraj

l.p.potharaju@student.tudelft.nl, msantiagopedro@tudelft.nl, pbasavaraj@tudelft.nl



Research background

- Fe-Ni(-Co) alloys utilize magneto-volume (Invar) effects to achieve a controlled or extremely low CTE, ensuring dimensional stability under temperature variations.
- Optical benches, sensor and instrument housings, precision mounts, and glass-to-metal hermetic seals in satellite electronics.
- While Fe-Ni alloys offer precise thermal expansion control (from ultra-low to glass-matched), they remain susceptible to thermo-mechanical and microstructural instability in space environments, motivating the evaluation of their long-term degradation limits.

Critical space conditions

- Thermal Extremes and Cycling**
CTE & Microstructure: alters the magnetic domain structure and causes CTE hysteresis.
- Radiation**
Microstructure: alters lattice defect populations, affecting the mechanical strength and fatigue resistance.
- Atomic Oxygen**
Oxidation: alters surface properties and, consequently, the thermo-optical properties.
- High Vacuum**
Residual Stress & Outgassing: promotes stress relaxation and can increase dimensional instability.


How can the intrinsic thermal and environmental degradation of Invar, Kovar, and Nilo 48 be mitigated to ensure long-term stability in critical space applications?

Material comparison

- Super Invar:** Lowest CTE due to magneto volume effect → highest dimensional stability; ideal for ultra-high-precision applications. [1]
- Kovar:** Ideal for application where controlled thermal expansion needed → Optimized for hermetic glass-to-metal sealing, with CTE matched to borosilicate glass with addition of Cobalt. [1]
- Nilo 48:** Preferred for high thermal stability, maintaining near-constant CTE over wide temperature ranges (up to ~460 °C).

Other observations:

In Fe-Ni material magneto volume effect peaks at 36% and further decreases to get vanished at 50% or more Ni which can be observed in NILO 48. [2]



Material Degradation Mechanism

- Thermal cycling with varying temperature regimes in space** is one of the dominant degradation driver caused with microstructural evolution and CTE drift. [3]
- Operating above the Curie temperature** leads to loss of ferromagnetic ordering, rapidly increasing CTE and dimensional instability.
- CTE mismatch** between structural materials and seals under these conditions can induce stress, fatigue, and eventual failure. [4]

State of art

- Operational Enveloping:** The primary industry standard is strict thermal governance to keep materials below their magnetic transition temperatures to preserve the Invar Effect. [5]
- Thermal Management via Plating:** Due to the low thermal conductivity of Fe-Ni alloys, high-conductivity coatings like Silver (Ag) or Copper are applied to dissipate heat. Gold plating (ASTM B488) is mandatory for optical sensing components to prevent surface oxidation degradation. [6,7]
- Active Regulation:** Current missions rely on heavy active cooling loops or physical isolation (heat shunts) to mechanically decouple the alloy structure from hot electronics.

-----Our perspective on the state of art-----



Necessity of Surface Engineering: We agree that surface plating (Ag/Au) is unavoidable. The intrinsic weakness of Fe-Ni alloys (low thermal conductivity + high oxidation susceptibility) cannot be solved by bulk alloy design without destroying the magnetic stoichiometry required for low CTE.



Reliance on Passive Isolation: We disagree with the literature's reliance on passive "insulation" or "shields." Structural components often must physically bridge hot and cold sections, making total isolation impossible. Furthermore, organic coatings for thermal control risk outgassing and are inferior to metallic solutions.

Proposed own solutions

Mission:
Autonomous Curie -
Limit Throttling

Instead of static shielding, implement active sensors. If a component approaches its specific inflection point, the satellite software automatically throttles down nearby high-power instruments to reduce heat load.

Manufacturing:
Internal Cooling
Channels

Use Laser Powder Bed Fusion to create complex micro-channels inside the structural struts. This allows for fluid cooling or heat pipes directly within the material, far more efficient than external conductive plating.

Structure: Metal
Matrix Composites

Reinforce the alloy matrix with inert, low-CTE particles (Carbon Nanotubes or SiC). This provides a physical constraint on thermal expansion that acts as a backup if the chemical Invar effect fails due to temperature spikes. [8]

Materials:
Functionally Graded
Materials

Develop components that transition from the specific Fe-Ni alloy at the interface (for sealing/precision) to a high-temperature superalloy in the bulk. This bypasses the "Curie limit" of the bulk structure while maintaining local CTE matching.

Conclusion

Fe-Ni alloys provide essential controlled and ultra-low thermal expansion for space precision, but their reliance on the thermally-limited Invar Effect creates vulnerability. Long-term stability requires moving beyond passive material selection to active thermal governance and multi-level structural engineering.

References: [1] [https://vulcanmetalgrou.com/low-expansion-alloys/#:~:text=It's%20used%20in%20ultra%2Dprecision,glass%2Dto%2Dmetal%20seals](https://vulcanmetalgrou.com/low-expansion-alloys/#:~:text=It's%20used%20in%20ultra%2Dprecision,glass%2Dto%2Dmetal%20seals;); [2] Sahoo, Ananya & Medicherla, V.. (2021). Fe-Ni Invar alloys: A review. Materials Today: Proceedings. 43. 10.1016/j.matpr.2020.12.527; [3] Gao, LY., Liu, ZQ. & Li, CF. Failure Mechanisms of SAC/Fe-Ni Solder Joints During Thermal Cycling. J. Electron. Mater. 46, 5338-5348 (2017); [4] J. Pavio and D. Hyde, "Effects of coefficient of thermal expansion mismatch on solder attached GaAs MMICs," 1991 IEEE MTT-S International Microwave Symposium Digest, Boston, MA, USA, 1991, pp. 1075-1078 vol.3, doi: 10.1109/MWSYM.1991.147200. [5] M. Takayama et al., "Thermal expansion characteristics of Super Invar," Trans. JIM, vol. 18, no. 3, pp. 32-38, 1975. [6] Z. Zhang et al., "Enhancing the thermal conductivity of Kovar alloys... incorporation of an Ag network," Mater. Lett., 2025. [7] "Standard Specification for Electrodeposited Coatings of Gold for Engineering Uses," ASTM B488-18, 2018. [8] Stephenson et al., "Physical and Mechanical Properties of LoVAR: a new lightweight particle-reinforced Fe-36Ni alloy," SPIE, 2015

