MASTER COPY

biomedical Limited	BIOMEDICAL LIMITED, NO 1 OHIMEGE ROAD, INDUSTRIAL ESTATE, ILORIN KWARA STATE, PMB 1499 PVC POUCH CERTIFICATE OF ANALYSIS (1000ml) **BML/QA/STP/PKF/007/F02**

Material Name: PVC Pouch (1000ml)	Batch No:	Pharmacopeia Ref: BP 2023/In-House
Manufacturer:	Supplier:	Logbook/Revision Number
MF. Date:	EX. Date:	Logbook page No.:
Sampled By:	Qty Received:	Logbook Volume:
Product Code: PKF007	No. of containers:	Analysed by:
QC. AR. No: PMF/AR/QC/ /P0	Test Completed Date:	SOP Ref. No: BML-QDG-QA-105

S/No.	Test	Specification	Result
1.	Description	A clear transparent, thick, flexible airtight PVC Pouch, with no lump or bulging.	
2.	Identification (% Ash Content)	Shall comply identification tests ($A_1 \leq 5.0$)	
3.	Acidity or Alkalinity	NMT 0.8ml of 0.01M HCL VS is required	
4.	Absorbance	NMT 0.2	
5.	Residue on Evaporation	NMT 2mg	
6.	Reducing Substance	The difference between the titration volumes is not greater than 3.0ml	
7.	Extractible Heavy Metals	NMT 2ppm	
8.	Air Tightness	When filled with air at 8.0psi, there should be no bubble when immersed in water	
9.	Colour Check	As per the approved ART WORK for the product	
10.	Lettering and spelling check	There should be no wrong spellings and the lettering must be legible	
11.	Edge to edge Length	29.50 – 31.00cm	
12.	Edge to Edge Breadth	11.50 – 12. 50cm	
13.	Neck Tube Length	4.50 – 5.50 cm	
14.	Flying wing Neck Length	4.50 – 5.50 cm	
15.	Ink Lifting Test	No ink must be lifted with Tape and when Autoclaved there should be no ink lifting or smulging	

CONTROL COPY

MASTER COPY

biomedical Limited	BIOMEDICAL LIMITED, NO 1 OHIMEGE ROAD, INDUSTRIAL ESTATE, ILORIN KWARA STATE, PMB 1499 PVC POUCH CERTIFICATE OF ANALYSIS (1000ml) BML/QA/STP/PKF/007/F02

16.	Welding Joint Length	2.00 – 2.50cm	
17.	Neck Tube Diameter	0.75- 0.85cm	
18.	Welding Joint thickness	1.00- 1.40 mm	
19.	Leakage Test	There should not be any form of leakages. Should be able to withstand temperature up to 122°C and 2.5 Bar pressure	
20.	Fill Volume Test	1000 – 1050ml	
21.	PVC Weight	35.50 – 38.00g	
22.	PVC Thickness	0.80 – 1.0mm	
23.	Total Bacteria Count	Must be sterile	
24.	Total Yeast & Moulds Count	Must be sterile	
25.	Pathogens	Must be absent	
26.	Pyrogen	Pyrogen Free	

CHECKER's VERDICT (box option) : **RELEASED / FAILED / HOLD / REPEAT**

Remark:

Analyst(chemist):	**Analyst(microbiologist):**	**Reviewed By: QCH**	**Approved By: QAM**
Sign:	**Sign:**	**Sign:**	**Sign:**
Date:	**Date:**	**Date:**	**Date:**

CONTROL COPY