

# TECHNICAL DATASHEET

# SUPER VINYL SATIN EMULSION – LOW VOC

## PRODUCT DESCRIPTION

Super Vinyl Matt – low VOC emulsion is a vinyl acrylic paint designed for interior and exterior walls and ceilings. It provides a long-lasting satin decorative finish with excellent protection and resistance properties.

## ENVIRONMENTAL STANDARDS & VOC REQUIREMENTS

This paint conforms to environmental standards, is free of toxic materials, solvents and has a VOC content value <1% complying with **ASTM D2369-20**

## PRODUCT BENEFITS

- 1- Non-toxic, Odorless & Non-flammable product.
- 2- Long lasting performance
- 3- Excellent leveling and coverage.
- 4- High Resistance to UV and various climatic conditions
- 5- Resistance to the alkalinity of concrete.
- 6- Water resistance
- 7- Water vapor permeability
- 8- Excellent washability

## RECOMMENDED USES

All interior and exterior walls and ceilings of concrete, masonry, stucco, fairfaced concrete, gypsum boards, non-chalking old paints, cement plaster, tyrolean, brick, concrete structures and facades.

## SURFACE PREPARATION

Surfaces should be solid, clean and dry, free from oil, grease, salt, dust and other contaminants. Alkaline and acid surfaces should be cleaned and neutralized.

Deteriorated previous coatings, weak and blistered paints or chalky substances should be removed by scrapers, paintremovers or flame spraying.

Non-disintegrated paints or glossy surfaces of previous coatings should be roughened slightly with sand paper to ensure good intercoat adhesion.

Pores and holes must be filled with Ready Putty before priming.

## PHYSICAL AND CHEMICAL PROPERTIES

### Physical Properties

Physical State Viscous

Appearance Gloss Finish

Color Range See Catalogue

Temperature 30°C

Relative Humidity 60%

Specific Gravity, ISO 2811 1.29 g/cm<sup>3</sup>

Viscosity, ISO 2884 4- 6 poises

pH 8- 9

Drying Time, ASTM D5894 2-4 hrs/coat

Recoat Time After 4- 6 hours

Coverage 50- 60 m<sup>2</sup> per US gallon per one coat

Opacity, ISO 6504-3 > 90%

Sag Resistance, ASTM D3730 Excellent

Leveling, ASTM D2801 Excellent

Scratching Resistance, ASTM D3003

### Chemical Properties

% Solids by Weight 50 ± 2 %

% Solids by Volume 64 ± 2%

Very low VOC <1%

### PRIMING/ THINNING/ APPLYING

Prime the surface with one coat of sealer (with a specific dilution depending on the surface condition).

Thin with clean water (20 – 30% for brush/roller application). Thickness of paint film depends on condition of surface.

Apply 2-3 coats depending on the color of the product.

Clean tools and equipment with water immediately after use.

## **PACKING**

In cylindrical tin containers of the following capacities:

- 1 US Quart = 0.95 L.
- 1 US gallon = 3.78 L.
- 1 Pail (5 U.S.G.) = 20L

## **STORAGE**

Avoid frost & excessive heat.

The technical information contained in this Technical Data Sheet is to be understood as advice only and not binding in any respect.  
All details about working with our products should be adapted to prevailing local conditions and materials used.