



P.O.Box: 85 – Zouk Mikhaël / Lebanon Tel.: +961 9 218 645 - +961 9 218 656

Fax: +961 9 220 215 www.Amazonapaints.com info@Happywallpaints.com

# **TECHNICAL DATASHEET**

# **POLYURETHANE SEALER**

#### PRODUCT DESCRIPTION

A two pack air-drying polyurethane sealer providing excellent sealing properties and sandability.

#### PRODUCT BENEFITS

- 1- Good mechanical resistance
- 2- Good intercoat adhesion
- 3- Excellent sandability
- 4- Good chemical resistance
- 5- High cracking resistance
- 6- Excellent sealing properties
- 7- Good weathering resistance

# **RECOMMENDED USES**

Interior and Exterior heavy duty sealer for applications where high performance, excellent abrasion, chemical and mechanical resistance are required. Ideal for wood surfaces and can also be applied on metallic substrates.

### SURFACE PREPARATION

Surfaces must be dry and clean, free from oil, greases and other contaminations. Previous chalking, flaking or deteriorated coatings should be removed. Holes and crevices must be properly filled. Humidity of wood should not exceed 18- 20%

# PHYSICAL AND CHEMICAL PROPERTIES

# **Physical Properties**

Technology Polyurethane Physical State Viscous Liquid

Appearance Comp. A translucent liquid

Comp. B clear liquid







P.O.Box: 85 – Zouk Mikhaël / Lebanon Tel.: +961 9 218 645 - +961 9 218 656

Fax: +961 9 220 215 www.Amazonapaints.com info@Happywallpaints.com

# Two Components- requires mixing

Color Clear

Component A

Specific Gravity, ISO 2811  $1 \pm 0.05$  g/cm<sup>3</sup> (Gloss Finish),

Viscosity, ISO Cup 4 260-280 sec

Component A+B

Drying Time, ASTM D 5895

Wet Film Thickness, ISO 2808

Dry Film Thickness, ISO 2808

Recoat Time

Coverage

30 min to touch.

100 - 150µm per coat

50-75µm per coat

After 2- 3 hours

12- 15 m²/liter

Sag Resistance, ASTM D 3730 Excellent Leveling, ASTM D 2801 Excellent

Scratching Resistance, ASTM D3002, D 3359 Excellent

# **Chemical Properties**

# Component A

% Solids by Weight
 47- 49%
 Solids by Volume
 42- 44 %

#### THINNING/ APPLYING

Mix Component A with Component B (50% hardener) Allow the mixture to react for 10- 15 min Thin with 20- 25% PU thinner

Apply one coat on the substrate.

Wait 6-8 hours before sanding.

Tools: brush, Roller, Spray

Clean tools and equipment with PU Thinner immediately after use.

# **CAUTION**

Flammable liquid. Keep away from flame or high heat.

Avoid inhalation of spray mist and arrange for adequate spraying precautions especially in closed areas.





P.O.Box: 85 – Zouk Mikhaël / Lebanon Tel.: +961 9 218 645 - +961 9 218 656

Fax: +961 9 220 215 www.Amazonapaints.com info@Happywallpaints.com

# **PACKING**

In cylindrical tin containers of the following capacities:

- 1 US Quart = 0.95 L.
- 1 US gallon = 3.78 L.
- 1 Pail (5 U.S.G.) = 20L

Each container is supplied with its appropriate hardener and Thinner

# **STORAGE**

1 year under normal storage conditions from the issue date. Avoid frost & excessive heat.

The technical information contained in this Technical Data Sheet is to be understood as advice only and not binding in any respect.

All details about working with our products should be adapted to prevailing local conditions and materials used.