


	ADBD lab Test Report	R024591	PAXAR Bangladesh Ltd. A subsidiary of Avery Dennison Corporation Plot#167-169, Dhaka-EPZ-Ext. Area Savar, Dhaka-1349, Bangladesh
Doc.Update date:	7/16/2020	Revision No.	15.6
Sample received date	5/16/2026	Report update Date	5/19/2026
Order informations details: The following samples is identified on behalf of the customer as:			
RBO	WALMART	Customer name	THE ROSE
Item Number	WNMU38012-LIGHT TURQUISE HALO	SO +Line	138307125+1.1
Customer P.O Number	ITSL-00102	Fabric Color	Vintage light wash
Fabric composition	100% Cotton	Print Quality	AG
Bonding date	16-May-2026	Bonding side	Fabric Back side
Bonding parameters setting details			
Temperature (° C)	160	Peel method	Cold
Line Pressure	6.4	Silicon type	soft
Applied Pressure(kg/cm ²)	2	Fabric attached	NO
Dwell time	10	Need to Use Stream	No
Silicon size	26x38	Bonded by	Lovelu Mia
Bonding machine model	Insta 718	If model no is changed then may need to changed bonding parameters.	
Bonding comments			
NB: Applied Pressure calculation =	3.14 X Piston radius ² (cm ²) X air pressure kg/cm ² into cylinder		
	Platen size cm ² (Lenght *Width)		
Tracking No	<u>TR-21301</u>	Folder no	
Durability/Appearance Wash: AATCC 135	Fail-Don't go for Bulk		
Lab Comments	Peeling off		
Approved By		Mohammad Delwar Hossan	
			
"Avery Dennison RBIS is committed to providing quality product services on time and inconformance to requirements for customer satisfaction at all times.Additionally it is prohibited the undue influence oever third party laboratories from employees to alter test methods ot test result that serve as th ebasis for certifying a products compliance under federal law of every site location. Achievement of this objectives requires us to establish and maintain an effective quality system that aims at superior preformance, while conforming to all product safety, environment and legal requirement.we review quality improvment as a continous process abd will provide training and create an environment for employees to conform to standards and customer requirements. we will also aim at building long-term partnership with our customers and suppliers."			

	ADBD lab Test Report	R024591	PAXAR Bangladesh Ltd. A subsidiary of Avery Dennison Corporation Plot#167-169, Dhaka-EPZ-Ext. Area Savar, Dhaka-1349, Bangladesh
Standard:Home laundry: Durability/Appearance Wash: AATCC 135, washing temp: "40 +/- 2 °C 104 +/- 4 °F", No. of Washing Cycles: 3 cycles / 25 cycles, Washing Duration per cycle: 40 mins, Washing Machine: Home laundry machine, Detergent: Liquid Tide Regular detergent: 46 grams/cycle.", Load Weight: 1.8 kg, Drying: Tumble dry low, Dry and wash cycle: Dry @3, 25 cycles, Wash program: Normal.			
Test Assessment criteria:			
1. Cracking	☐	5. Illegibility/ Hazy appearance	☐
2. Peeling off/ Loose Edges	☒	6. Wrinkles	☐
3. Bubbling Effect	☐	7. Reflective or Special Effects missing	☐
4. Poor color retention or color fading	☐		
Gray Scale of Passing Grade of Colour Change (3.5 or above)		Acheived	4.0
Gray Scale of Passing Grade of Colour Stain		NA	

UNTESTED SAMPLE**TESTED SAMPLE (25 Cycles)**

REPORT END