


Crocking/ rubbing test			
Order informations details: The following samples is identified on behalf of the customer as:			
Report no:		Date:	5/17/2026
RBO:	UNIQLO	Reference	BS00164AD-JP38QA3 J
Test type	RBO standard Test	Eng no/FS no:	S4237226-1
Customer name	Paxar BD Ltd.	Ink Name	WRB120
Product line	RFID	Requested date	5/16/2026
Material name	5-605701-000-01		
Hangtags/ Stickers			
Colour Fastness to rubbing: JIS L 0849			
Standard and parameters	Colour Fastness to rubbing: JIS L 0849		
	RT-200Tester (GAKUSIN type), Temperature: N/A, No of crocking times: 100 cycles, barcode grading before and after crocking/mins: B or above, Color stain fabric: white, Rubbing distance 10 cm. Load: 2 N(2)		
Gray Scale of Passing Grade of Colour stain (Dry)	Hangtags:		
	4.0 or above		
	*Printing should not be faded or become blur after rubbing.		
	Stickers:		
Gray Scale of Passing Grade of Colour stain (Wet)	4.5 or above		
	*Printing should not be faded after rubbing.		
Test Result			
Result	Pass		
Lab comment			
Original sample	Dry Rub test		Crock Meter sample
			


Dry Rubbing grade.....5.0.....

Tracking no

2333

Approved by





PAXAR Bangladesh Ltd.

A subsidiary of Avery Dennison Corporation
Plot#167-169, Dhaka-EPZ-Ext. Area
Savar, Dhaka-1349, Bangladesh

Crocking Test

Order informations details: The following samples is identified on behalf of the customer as:

Report no:	TRF-2386	Date:	17-May-2026
RBO:	ZARA	Reference	CLZCALL053
Test type	Only Rubbing/ Crocking	Eng no/FS no:	S4239674-1
Customer name	Paxar BD Ltd.	Ink Name	DC1181
Product line	RFID	Requested date	5/16/2026 14:22:59
Material name	4-258907-000-00		

EQUIPMENT

- Crockmeter/crockmaster (automatically or manually operated; or extra rubbing finger (accessories only)
- Cotton rubbing cloth (5cm x 5cm),
- Grey scale for assessing staining

Test result

Result:	Pass		
Lab Comments :			
Standard	Colorfastness to crocking: ISO 105X12		Crocking cycles 10 cycles
Original sample	Dry Rub (Passing grade 4)	Wet Rub (Passing grade 3)	Crock meter sample
			Dry Crockmeter Sample
			

Dry Rubbing grade5.....

Wet Rubbing grade4-5.....

Tracking no

2334

Approved by


Crocking/ rubbing test			
Order informations details: The following samples is identified on behalf of the customer as:			
Report no:	TRF- 2385 	Date:	5/17/2026
RBO:	UNIQLO	Reference	BS00164AD-JP38QA3 J
Test type	RBO standard Test	Eng no/FS no:	S4237226-1
Customer name	Paxar BD Ltd.	Ink Name	WRB120
Product line	RFID	Requested date	5/16/2026
Material name	5-605701-000-01		
Hangtags/ Stickers			
Colour Fastness to rubbing: JIS L 0849			
Standard and parameters	Colour Fastness to rubbing: JIS L 0849		
	RT-200Tester (GAKUSIN type), Temperature: N/A, No of crocking times: 100 cycles, barcode grading before and after crocking/mins: B or above, Color stain fabric: white, Rubbing distance 10 cm. Load: 2 N ₂)		
Gray Scale of Passing Grade of Colour stain (Dry)	Hangtags:		
	4.0 or above		
	*Printing should not be faded or become blur after rubbing.		
	Stickers:		
Gray Scale of Passing Grade of Colour stain (Wet)	4.5 or above		
	*Printing should not be faded after rubbing.		
Test Result			
Result	Pass		
Lab comment			
Original sample	Dry Rub test		Crock Meter sample
			

Dry Rubbing grade.....5.0.....

Tracking no

2333

Approved by




Crocking/ rubbing test			
Order informations details: The following samples is identified on behalf of the customer as:			
Report no:		Date:	5/17/2026
RBO:	UNIQLO	Reference	BS00164AD-JP38QA3 J
Test type	RBO standard Test	Eng no/FS no:	S4237226-1
Customer name	Paxar BD Ltd.	Ink Name	WRB120
Product line	RFID	Requested date	5/16/2026
Material name	5-605701-000-01		
Hangtags/ Stickers			
Colour Fastness to rubbing: JIS L 0849			
Standard and parameters	Colour Fastness to rubbing: JIS L 0849		
	RT-200Tester (GAKUSIN type), Temperature: N/A, No of crocking times: 100 cycles, barcode grading before and after crocking/mins: B or above, Color stain fabric: white, Rubbing distance 10 cm. Load: 2 N(2)		
Gray Scale of Passing Grade of Colour stain (Dry)	Hangtags:		
	4.0 or above		
	*Printing should not be faded or become blur after rubbing.		
	Stickers:		
Gray Scale of Passing Grade of Colour stain (Wet)	4.5 or above		
	*Printing should not be faded after rubbing.		
Test Result			
Result	Pass		
Lab comment			
Original sample	Dry Rub test		Crock Meter sample
			


Dry Rubbing grade.....5.0.....

Tracking no

2333

Approved by





PAXAR Bangladesh Ltd.

A subsidiary of Avery Dennison Corporation
Plot#167-169, Dhaka-EPZ-Ext. Area
Savar, Dhaka-1349, Bangladesh

Crocking Test

Order informations details: The following samples is identified on behalf of the customer as:

Report no:	TRF-2386	Date:	17-May-2026
RBO:	ZARA	Reference	CLZCALL053
Test type	Only Rubbing/ Crocking	Eng no/FS no:	S4239674-1
Customer name	Paxar BD Ltd.	Ink Name	DC1181
Product line	RFID	Requested date	5/16/2026 14:22:59
Material name	4-258907-000-00		

EQUIPMENT

- Crockmeter/crockmaster (automatically or manually operated; or extra rubbing finger (accessories only)
- Cotton rubbing cloth (5cm x 5cm),
- Grey scale for assessing staining

Test result

Result:	Pass		
Lab Comments :			
Standard	Colorfastness to crocking: ISO 105X12		Crocking cycles 10 cycles
Original sample	Dry Rub (Passing grade 4)	Wet Rub (Passing grade 3)	Crock meter sample
			Dry Crockmeter Sample
			

Dry Rubbing grade5.....

Wet Rubbing grade4-5.....

Tracking no

2334

Approved by


Crocking/ rubbing test			
Order informations details: The following samples is identified on behalf of the customer as:			
Report no:	TRF- 2385 	Date:	5/17/2026
RBO:	UNIQLO	Reference	BS00164AD-JP38QA3 J
Test type	RBO standard Test	Eng no/FS no:	S4237226-1
Customer name	Paxar BD Ltd.	Ink Name	WRB120
Product line	RFID	Requested date	5/16/2026
Material name	5-605701-000-01		
Hangtags/ Stickers			
Colour Fastness to rubbing: JIS L 0849			
Standard and parameters	Colour Fastness to rubbing: JIS L 0849		
	RT-200Tester (GAKUSIN type), Temperature: N/A, No of crocking times: 100 cycles, barcode grading before and after crocking/mins: B or above, Color stain fabric: white, Rubbing distance 10 cm. Load: 2 N ₂)		
Gray Scale of Passing Grade of Colour stain (Dry)	Hangtags:		
	4.0 or above		
	*Printing should not be faded or become blur after rubbing.		
	Stickers:		
Gray Scale of Passing Grade of Colour stain (Wet)	4.5 or above		
	*Printing should not be faded after rubbing.		
Test Result			
Result	Pass		
Lab comment			
Original sample	Dry Rub test		Crock Meter sample
			

Dry Rubbing grade.....5.0.....

Tracking no

2333

Approved by



Crocking/ rubbing test			
Order informations details: The following samples is identified on behalf of the customer as:			
Report no:		Date:	5/17/2026
RBO:	UNIQLO	Reference	BS00164AD-JP38QA3 J
Test type	RBO standard Test	Eng no/FS no:	S4237226-1
Customer name	Paxar BD Ltd.	Ink Name	WRB120
Product line	RFID	Requested date	5/16/2026
Material name	5-605701-000-01		
Hangtags/ Stickers			
Colour Fastness to rubbing: JIS L 0849			
Standard and parameters	Colour Fastness to rubbing: JIS L 0849		
	RT-200Tester (GAKUSIN type), Temperature: N/A, No of crocking times: 100 cycles, barcode grading before and after crocking/mins: B or above, Color stain fabric: white, Rubbing distance 10 cm. Load: 2 N(2)		
Gray Scale of Passing Grade of Colour stain (Dry)	Hangtags:		
	4.0 or above		
	*Printing should not be faded or become blur after rubbing.		
	Stickers:		
Gray Scale of Passing Grade of Colour stain (Wet)	4.5 or above		
	*Printing should not be faded after rubbing.		
Test Result			
Result	Pass		
Lab comment			
Original sample	Dry Rub test		Crock Meter sample
			

Dry Rubbing grade.....5.0.....

Tracking no

2333

Approved by

