



Document update	7/9/2021	Version	8.1
Report no	ADBD16052026-POLO-A2792	Report Date:	16-May-2026
Test start time	12-May-2026	Test end Time	16-May-2026

Adhesive performance test Report

Standard	Peel-off Test for Stickers used on Fabric or Cap Bill (GPNC-PPR-OP-002)
Equipment and Materials:	1. Humidity Chamber on a continuous 48 hours schedule. 2. Fabric / Cap bill
Preparation of Chamber	1. Set temperature to 70°C & humidity setting to 80% (for high temperature & humidity peel off test) 2. Set temperature to 0°C

Order Information

Vendor name	POLO - RALPH LAUREN	Item	HKSBDML4810B(R110) / HKSBDML4810W(R110)
Fabric name	Tuscan Beige Heather	Customer name	Epyllion Style-GAZIPUR
Fabric composition	100% Cotton Double Jersey Jacquard	Sticker attached side	Face Side
Sam's project ID		Request date	06-May-2026
GPD/ CS name	Main Uddin	Fabric received date	12-May-2026
Adhesive Material name	APR-SY0083-330-2435 60u APPAREL FILM CLEAR/ R115 REMOVABLE/ BG50 WHT IMP(SY0083)-330MM		

Evaluation Criteria of peel off test		Result
The whole sticker peel off		✓
Both two edges peel off ≥2mm (If one edge peel-off<2mm and one edge peel-off ≥2mm, it is a "pass" result)		✓
One edge peel off ≥5mm		✓
Result	Pass	
Comments		

Note: If peel off test is fail, then no need for aging test.

Equipment and Materials:	Humidity Chamber, 10 lbs weight, Plastic Film, Fabric, 70°C & humidity as 80% 48 hours	
Aging test evaluation criteria		Evaluation result
1.Visible adhesive residue on fabric/ cap bill. Minimum requirement is no visible residue.		✓
2.Invisible adhesive residue on fabric/ cap bill. Minimum requirement is no invisible residue (i.e. no tacky feel).		✓
3.Damage on fabric/cap bill structure (fabric/cap bill relaxing or fiber pull). Minimum requirement is no damage on fabric.		✓
4.Color change/loss of the sticker, inspected by using an AATCC Gray Scale for Color Change under D50 light source. Minimum passing grade is 4.		✓
5.Sticker Peel Off (sticker falling off the fabric/cap bill without an external force). Min requirement is no sticker peel off.		✓
Result	Pass	
Reason of Fail		
Lab Comment		

Tracking

2712

Approved by

Report no

ADBD16052026-POLO-A2792

Date:

16-May-2026

Specimen of Peel Off Test

Control Sample



Low Temp Tested sample



High Temp Tested sample



Report no**ADBD16052026-POLO-A2792****Date:****16-May-2026****Specimen of Aging test****Tested specimen**