


PAXAR Bangladesh Ltd.
A subsidiary of Avery Dennison Corporation
Plot#167-169, Dhaka-EPZ-Ext. Area
Savar, Dhaka-1349, Bangladesh

Sample Inspection card_Raw data sheet

Date	18-May-2026	Report number	ADL18052026-4558
RBO	G.U. CO., LTD.	SO	138494156+1.1
Item	WC00759AD-JP		
Result	Pass	Fail	Observation
Lab Commnets	Fraying		
Test Standard Name	JIS L1930 C4M Modified		

Control Sample	Tested samples
Technican Signature	Review By

Tracking No	454
-------------	-----



PAXAR Bangladesh Ltd.

A subsidiary of Avery Dennison Corporation
Plot#167-169, Dhaka-EPZ-Ext. Area
Savar, Dhaka-1349, Bangladesh

Crocking Test

Order informations details: The following samples is identified on behalf of the customer as:

Report no:	TRF-2389	Date:	19-May-2026
RBO:	KONTOOR BRANDS	Reference	7BAR011
Test type	RBO standard Test	Eng no/FS no:	S4244839-1
Customer name	Paxar BD Ltd.	Ink Name	Z203
Product line	RFID	Requested date	19-May-2026
Material name	5-607738-000-01		

EQUIPMENT

- Crockmeter/crockmaster (automatically or manually operated; or extra rubbing finger (accessories only)
- Cotton rubbing cloth (5cm x 5cm),
- Grey scale for assessing staining

Test result

Result:	Pass
Lab Comments :	

Standard	Colorfastness to crocking: AATCC 8	Crocking cycles	10 cycles
Original sample	Dry Rub (Passing grade 4.0)	Crock meter sample	


--	--	--

Dry Rubbing grade4.0.....

Tracking no

2337

Approved by



PAXAR Bangladesh Ltd.
A subsidiary of Avery Dennison Corporation
Plot#167-169, Dhaka-EPZ-Ext. Area
Savar, Dhaka-1349, Bangladesh

Crocking Test

Order informations details: The following samples is identified on behalf of the customer as:

Report no:	TRF-2388	Date:	19-May-2026
RBO:	COMPTOIR DES COTONNIERS(CDC)	Reference	PTT-RFIDSTCK
Test type	RBO standard Test	Eng no/FS no:	S4244838-1
Customer name	Paxar BD Ltd.	Ink Name	Z203
Product line	RFID	Requested date	19-May-2026
Material name	5-607108-000-01		

EQUIPMENT

- Crockmeter/crockmaster (automatically or manually operated; or extra rubbing finger (accessories only)
- Cotton rubbing cloth (5cm x 5cm),
- Grey scale for assessing staining

Test result

Result:	Pass
Lab Comments :	

Standard	Colorfastness to crocking: AATCC 8	Crocking cycles	10 cycles
Original sample	Dry Rub (Passing grade 4.0)	Crock meter sample	

Dry Rubbing grade4.5.....

Tracking no

2336

Approved by