




PAXAR Bangladesh Ltd.

A subsidiary of Avery Dennison Corporation  
Plot#167-169, Dhaka-EPZ-Ext. Area  
Savar, Dhaka-1349, Bangladesh

## Crocking Test

Order informations details: The following samples is identified on behalf of the customer as:

|               |                        |                |                    |
|---------------|------------------------|----------------|--------------------|
| Report no:    | TRF-2386               | Date:          | 17-May-2026        |
| RBO:          | ZARA                   | Reference      | CLZCALL053         |
| Test type     | Only Rubbing/ Crocking | Eng no/FS no:  | S4239674-1         |
| Customer name | Paxar BD Ltd.          | Ink Name       | DC1181             |
| Product line  | RFID                   | Requested date | 5/16/2026 14:22:59 |
| Material name | 4-258907-000-00        |                |                    |

### EQUIPMENT

- Crockmeter/crockmaster (automatically or manually operated; or extra rubbing finger (accessories only)
- Cotton rubbing cloth (5cm x 5cm),
- Grey scale for assessing staining

### Test result

|                                                                                     |                                                                                     |                                                                                       |                                                                                       |
|-------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|
| Result:                                                                             | Pass                                                                                |                                                                                       |                                                                                       |
| Lab Comments :                                                                      |                                                                                     |                                                                                       |                                                                                       |
| Standard                                                                            | Colorfastness to crocking: ISO 105X12                                               |                                                                                       | Crocking cycles 10 cycles                                                             |
| Original sample                                                                     | Dry Rub (Passing grade 4)                                                           | Wet Rub (Passing grade 3)                                                             | Crock meter sample                                                                    |
|  |  |  | Dry Crockmeter Sample                                                                 |
|                                                                                     |                                                                                     |                                                                                       |  |

Dry Rubbing grade .....5.....

Wet Rubbing grade ....4-5.....

Tracking no

2334

Approved by