


$\text{Sr}_2\text{PrSbO}_6$ wide-gap double perovskite

$P2_1/c$ · monoclinic



triple stability


- ✓ dynamic
- ✓ mechanical
- ✓ thermodynamic

$$E_g = 5.09 \text{ eV}$$

$$B = 121.6 \text{ GPa}$$

$$\theta_D = 433 \text{ K}$$

$\alpha(\lambda)$ optical absorption



transport · thermal

$$ZT_{\text{max}} = 0.14$$

$$|S| = 200 \mu\text{V K}^{-1}$$

$$\kappa_L = 41.67 \text{ W m}^{-1} \text{ K}^{-1} @ 300\text{K}$$

