
RF01 temporary printed forming tool


Quantity1, PETG. One valid connected solid. Manufacturing geometry is in mm; this construction tool is not an escutcheon or a permanent insert.

RF01 / two views of the same exported temporary tool

Front / rigid forming face



Rear / projecting draft collar



Geometry and orientation

Cover-centered X right/Y up; +Z toward shower. Face outerD240, panel12 thick. Molding plastic faceZ+0.05; frontZ+12.05; collar rearZ-11.95. Collar front outer118.35x145.10 with semicircular ends; nominal wall2, depth12, draft1 degree smaller at rear. Minimum internal113.931x140.681. No threads or embedded fasteners.

Print and inspect

Flat front face on print bed; collar upward. Use solid bearing zones and dense face, without a hollow unsupported shell. Smooth and line molding face/outer collar; target molding-plane flatness0.3 mm. No certified force/temperature rating is implied. Read BOM, CHECKS and the setup sheet before field use.

Conditional readiness

Geometric STEP/STL read-back passed; actual support, full panel seating, print/liner coupon, hardware/service clearance and clean withdrawal remain dry checks before any filling. Do not order with the plate pair by default.