

Sample Code: 26M2707B2P	Nominal Size: 75 mm	Pipe Class: 3	Type: A
-------------------------	---------------------	---------------	---------

#	Clause	Parameter	Specified Requirement	Observed Value
1	10.1	Colour	As in CI 10.1	Satisfactory
2	10.1	Surface Finish	As in CI 10.1	Satisfactory
3	7.2.1.1 Table 3	Angle of taper (Note-1)	Specified : Shall not exceed 0 degree 30minute	Socket Inside diameter shall be measured by manufactureres only as per Note 2 of CI 7.2.1.1
4	5	CLASSIFICATION OF PIPES	Class 1/2/3/4/5/6	Class 3 (As declared)
5	5.2	The pipes shall be classified based on their application	a) Type A ? Pipes for water supply; and b) Type B ? Pipes for agricultural use.	A (As declared)
6	7	DIMENSIONS-PIPE-Nominal Diameter	Nominal Outside Diameter (Nominal Size)	75 (As declared)
7	7.1.1.1	DIMENSIONS-PIPE-Mean O.D. (Minimum)	75.0 mm,Min	1
8	7.1.1.1	DIMENSIONS-PIPE-Mean O.D. (Maximum)	75.3 mm, Max	11
9	7.1.1.1	DIMENSIONS-PIPE-Mean O.D. Variation	0.30 mm, max	1
10	7.1.1.2	DIMENSIONS-PIPE-O.D. at any Point (Minimum)	74.0 mm, Min	This requirement has not been checked according to foot note 1 of table 1
11	7.1.1.2	DIMENSIONS-PIPE-O.D. at any Point (Maximum)	76.0 mm, Max	This requirement has not been checked according to foot note 1 of table 1
12	7.1.1.2	DIMENSIONS-PIPE-Ovality (Maximum)	1.0	1
13	7.1.2.1	DIMENSIONS-PIPE-Thickness (Minimum)	2.6mm	1
14	7.1.2.1	DIMENSIONS-PIPE-Thickness (Maximum)	3.1mm	1
15	7.1.2.1	DIMENSIONS-PIPE-Average Thickness	3.1mm	1
16	7.2.1	DIMENSIONS-Socket		Satisfactory
17	7.2.1.1 Table 3	DIMENSIONS-Socket-Sockets for solvent cement jointing-Minimum Length	Socket Length (min): 44 mm	1
18	7.2.1.2 Table 4	DIMENSIONS-Sockets for elastomeric sealing ring joints-Socket inner Diameter	mm	NA
19	8	SEALING RINGS	Conforms With IS 5382	NA

Sample Code: 26M2707B2P		Nominal Size: 75 mm	Pipe Class: 3	Type: A
20	9.1	PIPE ENDS	The ends of the pipes meant for solvent cementing (both plain and bell ended) shall be cleanly cut and shall be reasonably square to the axis of the pipe or may be chamfered at the plain end	Full length not provided
21	10.1	PHYSICAL AND CHEMICAL CHARACTERISTICS-Visual Appearance	The colour of the pipes shall be light grey. Slight variations in the appearance of the colour are permitted.	Satisfactory
22	10.1.1	PHYSICAL AND CHEMICAL CHARACTERISTICS-Visual Appearance	The colour of the pipes shall be light grey. The internal and external surfaces of the pipe shall be smooth, clean and free from grooving and other defects.	Satisfactory
23	10.2	PHYSICAL AND CHEMICAL CHARACTERISTICS-Opacity	The wall of the plain pipe shall not transmit more than 0.2 percent of the visible light falling on it when tested in accordance with IS 12235 (Part 3).	1
24	11.1	MECHANICAL PROPERTIES-Reversion	Maximum: 5 %	1
25	11.2	MECHANICAL PROPERTIES-Vicat Softening Temperature	Min: 80 °C	more than 80 °C
26	11.2	MECHANICAL PROPERTIES-Resistance to External Blows at 0°C	Shall have a True Impact Rate of not more than 10.	Less than 10% TIR
27	11.3	MECHANICAL PROPERTIES-Density	1.40 and 1.46	1
28	11.1 Table 6	MECHANICAL PROPERTIES-Hydrostatic Pressure Test (Acceptance Test)	At Test pressure 4.19×0.6 MPa (min.) for 1 h the pipe shall not fail.	Pass
29	11.1 Table 7	MECHANICAL PROPERTIES-Hydrostatic Pressure Test (Acceptance Test)-for Integral Sealing Ring Sockets	The pipe shall not fail during the prescribed test duration	NA
30	11.1.1	MECHANICAL PROPERTIES-Hydrostatic Pressure Test (Acceptance Test)-for Plumbing pipes	The pipe shall not fail during the prescribed test duration	NA
31	13.1.2	MARKING	Type A shall additionally bear continuous longitudinal blue colour strip printing. These longitudinal blue colour strip shall be so placed so as to not merge/disturb the information marked on the pipes	Satisfactory