





- Cartulina estucada de frente blanco con dorso café.
- Hasta 72% de componente reciclado.
- 100% reciclable y biodegradable.

GRAMAJE g/m²	ESPESOR µm	RIGIDEZ (Taber 15°) gr.cm		COMPONENTE
		Longitudinal	Transversal	RECICLADO %
210	265	47	24	65
230	290	60	30	67
260	340	95	42	70
290	385	132	63	70
320	430	181	82	69
350	475	237	108	69
370	510	280	127	72
400	550	350	161	70

	l
HUMEDAD	8.0 %
COBB 60 Cupertina	20 - 80 g/m²
BLANCO ISO 2470	80

TOLERANCIAS			
± 5%			
± 5%			
- 15%			
± 5%			
± 1.5%			
± 2%			
-1+2 mm			
-1+2 mm			











