



Steel grades & specified Chemical Composition

The Chemical Composition of the steels are in accordance with below mentioned table.

The Chemical composition of these steels specified are integrated by grade numbers, are given for information only.

Elements not quoted in below table shall not be intentionally added to the steel without the agreement of the purchaser, other than the purpose of finishing the heat. All reasonable precautions will be taken to prevent the addition, from scrap or other material used in manufacturing of such elements which effect hardenability, mechanical properties and applicability.

Steel Grades			Chemical Composition, %								
Martensitic Steels											
A	-----	3	0.09 to 0.15	1	1	0.04	0.03 max	11.5 to 13.5	-----	1 max	-----
B	27	4	0.16 to 0.25	1	1	0.04	0.03 max	12 to 14	-----	1 max	-----
C	28	5	0.25 to 0.35	1	1	0.04	0.03 max	12 to 14	-----	1 max	-----
D	-----	-----	0.42 to 0.50	1	1	0.04	0.03 max	12.5 to 14.5	-----	1 max	-----
E	-----	-----	0.47 to 0.57	0.5	1	0.03	0.25 max	13.7 to 15.2	-----	0.5 max	-----
F	-----	-----	0.60 to 0.70	0.5	1	0.03	0.25 max	12 to 13.5	-----	0.5 max	-----
G	-----	-----	0.65 to 0.70	1	1	0.04	0.03 max	12 to 14	0.5 max	1 max	-----
H	-----	-----	0.35 to 0.40	1	1	0.045	0.03 max	14 to 15	0.8 to 0.6	-----	V:0.1 to 0.15
I	-----	-----	0.42 to 0.56	1	1	0.045	0.03 max	14 to 15	0.8 to 0.6	-----	V:0.1 to 0.15
K	30	-----	0.33 to 0.43	1	1	0.03	0.03 max	15 to 17	1 to 1.6	1 max	-----
N	-----	-----	0.85 to 0.95	1	1	0.015	0.03 max	17 to 19	0.8 to 1.3	-----	V:0.07 to 0.12
Ferritic Steels											
I	-----	8	0.08 mm	1	1.5	0.08	0.15 to 0.35	16 to 18	0.8 max	1 max	-----
Austenitic Steels											
Ref Letter	Grade Number according to standards		C	Si	Mn	P	S	Cr	Mo	Ni	Other Elements



DADDY D PRO

CARE FOR YOUR LIFE

M	-----	11	0.07 max	1	2	0.045	0.03 max	17 to 18	-----	8 to 11	-----
N	-----	17	0.12 max	1	2	0.08	0.15 to 0.35	17 to 18	-----	8 to 10	-----
O	-----	14	0.5 max	1	2	0.045	0.03 max	16 to 18	-----	6 to 8	-----
P	-----	20	0.07 max	1	2	0.045	0.03 max	16.5 to 18.5	2 to 2.5	10.5 to 13.5	-----

- The reference letters are used for the purpose of cross referencing
- The grade numbers are provisional and will be subject to alteration when the relevant international standards are published
- The manufacturer has the option of adding up to 0.7%

For and On Behalf Of
DADDY D PRO



Q.A Manager

Masjid e Aqsa, Ugoki Road Dattal, Sialkot - 51310, Pakistan

Phone: +92-52-3251203,

Fax: +92-52-3251204

mail: subayus1@aol.com, ddp786@hotmail.com, export@daddydpro.com, ddpmiami@hotmail.com

web: www.daddydpro.com