

TECHNICAL DATA SHEET

1. DESCRIPTION

Euroflex U is a flexography ink(also gravure) suited for the print of plastic film for lamination and potential subsequent heat treatment.

2. PRODUCT FEATURES

Euroflex U series presents:

- Excellent lamination characteristics with both a broad range of bi-and monocomponent solvent and solventless glues as well as in extrusion processes.
- Extremely high bond rates in relation to the adhesives used.
- Excellent printability.
- Low solvent retention.
- Perfect sealability on the print area of the laminated film.

The ink can develop nitrosamines with heat treatments above 120° C.

3. APPLICATIONS

Euroflex U suitable for the mirror printing of film for lamination.

It is necessary to add 4-5% of adhesion promoter to provide the adhesion on polyolefin film.

4. SUBSTRATES :

The Euroflex U series can be used on the following substrates:

- Pe Corona treated > 38 dynes/cm
- OPP,Coex OPP corona treated > 38 dynes/cm after addition of 4-5% adhesion promoter.
- Acrylic coated OPP
- PVdC coated PP (after previous tests)
- Corona treated PET > 48 dyne/cm .
- Chemical treated PET.
- PVdC coated PET(after previous tests)
- Corona treated OPA> 48 dyne/cm.

5. ADHESIVES

The Euroflex U series can be laminated with a broad range of mono and bicomponent solvent and solventless adhesives.

The actual bonding strength of the laminate strongly depends on the choice of substrate, adhesive and weight of the ink and the adhesive used.

Thus it is recommended that users carry out preliminary tests prior to industrial application. Euroink Distribution can provide assistance to confirm the suitability of the application, all the same it is recommended that preliminary tests are made on the ink/substrate specifications.

6. GENERAL HANDLING

6.1. Storage

- The Euroflex U series contains solvents considered highly inflammable; all due precautions should thus be taken.
- Temperature of storage: from 5°C to 35°C
- Shelf life: 12 months under above conditions

6.2. Waste disposal

- Care should be exercised in the disposal of printing ink waste. This should be carried out in accordance with good industrial practice, observing all the appropriate regulations and guidelines.

For more specific handling advice refer to the Safety Data Sheet (SDS).

7. PRINTING CONDITIONS

7.1. Printing Viscosities

Prior to use mix the product well and add the solvent required to obtain the right print viscosity. The optimum printing viscosity depends on press and running conditions. Good results have been achieved with these inks at the following viscosity:

- Gravure: 13-15 sec (Din cup N°4)
- Flexo: 16-25 sec (Din cup N°4)

7.2. Solvents

➤ Flexography (SOLIDS)

Normal: Mixtures of ethyl,i-propyl/ alcohol, i.propyl, n.propyl,ethyl /acetate, up to a ratio of 80/20

Slow: n-propyl alcohol, methoxypropanol, ethoxypropanol

➤ Flexography (PROCESS)

Normal: Mixtures of ethyl ,n-propyl/alcohol, i.propylic, n-propylic,ethyl/ acetate up to a ratio of 80/20

Slow: ethoxypropanol

➤ Gravure:

Fast: Ethyl acetate

Normal: Mixtures of ethyl, i.propyl, n-propyl alcohol/ethyl, isopropyl acetate, up to a ratio of 70/30

Slow: n-propyl alcohol, methoxypropanol

7.3. Wash up solvents

Mixture Alcohols / Esters

7.4. Cylinders / Plates

The Euroflex U series can be used with the top types of gravure cylinders and photopolymer plates used in flexography.

8. END-USE SAFETY

The good application of the inks depends on:

1. control of weight of applied ink
2. adequate drying on press
3. the correct structure of the laminate
4. correct design of the packaging
5. monitoring of all substances that might migrate from the ink and/or substrate
6. control of other parameters related to the article

Euroink Distribution can offer assistance in the handling of the above parameters.

Food packaging: in the event the printed packaging is for food contact it be reiterated that the entire processing chain is held responsible.

With particular regard to the potential migration of the substance from the printed packaging to the food contained therein the printer and the food packager have the prime responsibility of guaranteeing correspondence of the selfsame packaging to the regulations in force.

For its part Euroink Distribution will provide the customer all the information needed to highlight any potential risk of migration due to the inks.

9. DISCLAIMERS

The ink is not intended to direct food contact.

This list of applications, substrates and processes provided in this document is not exhaustive. Please contact your local Euroink Distribution representative for full technical evaluation of your application or process.

10. ASISTENTA TEHNICA/ CONTACT

For further information, please contact your local Euroink Distribution team.

5 January 2023

Our Products are intended for sale to professional users. The information herein is general information designed to assist customers in determining the suitability of our products for their applications. All recommendations are made without guarantee, since the application and conditions of use are beyond our control. We recommend that customers satisfy themselves that each product meets their requirements in all respects before commencing a print run. There is no implied warranty of merchantability or fitness for purpose of the product or products described herein. In no event shall Euroink Distribution be liable for damages of any nature arising out of the use or reliance upon this information. Modifications of the product for reasons of improvements might be made without further notice.

This form is valid without signature.