

The SocioEconomic Aspects of Stock Assessments

*Recommendations for Increasing Assessment Accuracy and Improving
Management Advice*

ME123

cell1	cell2	cell3
cell4	cell5	cell6
cell7	cell8	cell9

Obsah

Introduction	1
More Information	1
Vstupné údaje	1
Materiálové vlastnosti	1

Introduction

TODO Create an example file that demonstrates the formatting and features of your format.

More Information

You can learn more about controlling the appearance of PDF output here: <https://quarto.org/docs/output-formats/pdf-basics.html>

Vstupné údaje

Tabuľka 1: Vstupné údaje

	od	t_nom	p_op	temp_op	material
membranova-stena	57	5	10	315	12022
strop-ohniska	57	5	10	315	12022
strop-medzitahu	57	5	10	305	12022
zadna-stena-2-tah	57	5	10	260	12022
p-l-stena-2-tah	57	5	10	260	12022
vystupny-prehrievac	57	5	10	525	15128
salavy-prehrievac	57	5	10	480	15128
mreza	57	5	10	325	12022

Materiálové vlastnosti

Materiál 12022

Teplotný rozsah

$$T_{12022} = [20, 100, 200, 250, 300, 350, 400, 450]$$

Medza klzu

$$R_{p02-12022} = [255, 245, 225, 205, 177, 157, 137, 117]$$

Medza pevnosti

$$R_{m-12022} = 440$$

Medza pevnosti pri tečení (200 000 h)

Teplotný rozsah

$$T_{t-12022} = [380, 400, 420, 440, 460, 480, 500]$$

Medza pevnosti pri tečení

$$R_{mt-12022} = [145, 115, 89, 67, 48, 33.4, 24]$$

Materiál 15128

Teplotný rozsah

$$T_{15128} = [20, 200, 250, 300, 350, 400, 450, 500, 550, 600]$$

Medza klzu

$$R_{p02-15128} = [365, 319, 304, 294, 279, 265, 245, 226, 206, 181]$$

Medza pevnosti

$$R_{m-15128} = 490$$

Medza pevnosti pri tečení (200 000 h)

Teplotný rozsah

$$T_{t-15128} = [480, 500, 520, 540, 560, 580, 6500]$$

Medza pevnosti pri tečení

$$R_{mt-15128} = [197, 151, 115, 87, 66, 50, 38]$$