

CMTH-VVEDENSKY-3

IMPERIAL COLLEGE LONDON

DEPARTMENT OF PHYSICS

**A group-theoretical treatment of
first-order perturbations of potential
boundaries in semiconducting
nanocrystals**

Author:

Michal Horanský

Supervisor:

Dimitri D. Vvedensky

Assessor:

Jing Zhang

Word count: 2450

Date: April 6, 2024

1 Layperson's summary

Breaking the Symmetry, or, When Crystals Are Almost Perfect

The title of the layperson's summary: "Breaking the Symmetry, or, When Crystals Are Almost Perfect". It will focus firstly on the role of symmetries in selection rules and secondly on the overlap decomposition as a quantifier of what we mean by *approximate*. Technicalities such as double groups or growth of QDs shall be omitted for brevity (although [3] will be discussed as a motivator for the perturbative approach).

2 Abstract

In this project, we investigate the photonic properties of quantum dots employing a group-theoretical description of first-order perturbation theory. Experimental data from polarisation resolved photoluminescence spectroscopy are investigated using the theory of exciton complexes and group theory. The major features of the spectral diagrams can be labelled by exciton state transitions immediately by considering the total angular momentum coupling of these exciton complexes. These major features also exhibit splitting caused by crystallographic symmetry breaking. The transitions between said energy levels are subject to symmetry selection rules, and we attempt to quantify the rates of these transitions by considering approximate symmetries. A list of other effects that may cause symmetry elevation is stated and reviewed.

3 Contents

1	Layperson's summary	1
2	Abstract	2
3	Contents	3
4	Introduction	4
5	Discussions of theory employed	5
5.1	The InGaAs pyramidal quantum dot	5
5.2	Exciton complexes and double groups	5
5.2.1	Envelope function method	6
5.2.2	Symmetry arguments, group theory, and double groups	10
5.2.3	Total angular momentum coupling and Pauli's exclusion principle	13
5.3	Photoluminescence spectrum and evidence of symmetry elevation . .	13
6	Results	14
6.1	Treatment of parity	14
6.2	Symmetry suppression theory	14
7	Discussion of results	15
7.1	Symmetry suppression in pyramidal quantum dots	15
7.2	Other hypothetical causes of symmetry elevation	15
8	Conclusions	16
9	Acknowledgements	17
10	Bibliography	18

4 Introduction

Firstly, a historical context of the problem and a brief literature review (namely [1]). Secondly, a brief review of [3] as a *de facto* solution to symmetry elevation, and then motivating the need for a perturbative analysis under strain and imperfect growth, which favour the three pyramid-defined directions out of the six grown. Thirdly, a list of proposed solutions, with the first one, a perturbative model of a low-symmetry Hamiltonian being mathematically explored and quantified.

5 Discussions of theory employed

5.1 The InGaAs pyramidal quantum dot

A brief description of the growth process as employed by Karlsson, Pelucchi etc. A discussion of [3] and its arguments for the true shape. A review of effects that alter the shape (and hence the symmetry) of a quantum dot, including strain and other mechanical effects.

5.2 Exciton complexes and double groups

A theoretical description of exciton complexes, the decomposition of their wavefunctions into a periodic function and an envelope function, and a model of the envelope function's "effective Hamiltonian" as a box (of a non-rectangular shape) potential with particles interacting via Coulomb interaction and magnetic momenta interaction (here we justify a first-quantization approach by asserting non-relativistic effective speeds). Total angular momentum is shown to be a good quantum number and its treatment within the full rotoinversion $SU(2) \otimes C_i$ group is described.

NOTES:

- In the semi-classical tight-binding model, we consider excited fermions in the nanocrystal as "particles in a box", confined to a spatial domain in which they move freely, and the effects of the atomic structure on the free particles are encoded in the effective mass parameter.
- We can use the effective mass formulation because the nanocrystals are big enough to have a band-structure (cite Dresselhaus).
- The full wavefunction $\Psi(\vec{r})$ is decomposed into an envelope function $\Upsilon(\vec{r})$ and a periodic function $U(\vec{r})$, where $U(\vec{r} - \vec{r}_n) = U(\vec{r})$. Therefore

$$\Psi(\vec{r}) = \Upsilon(\vec{r}) U(\vec{r})$$

and therefore the character of the wavefunction under a rotation \hat{R} is

$$\chi^{(\Psi(\vec{r}))}(\hat{R}) = \chi^{(\Upsilon(\vec{r}))}(\hat{R}) \chi^{(U(\vec{r}))}(\hat{R})$$

Due to energy constraints, we expect the envelope functions to be dominated by the ground state levels, which transform according to the identity irrep. The character of the periodic function is then given by taking the total angular momentum eigenstate j and subduing it into the spatial point group of the quantum dot (which governs also the boundary conditions of the envelope function).

- Luttinger-Kohn model to justify free-electrons and effective masses at the Γ point (only there!!!!).

TEXT

The physical phenomenon which is subject to our study is photoluminescence. Since this mechanism does not have the QDs in a laboratory ensemble interact or "communicate", we can formulate a theoretical model of photoluminescence on a singular QD. An external electromagnetic field in the form of a light-beam interacts with the QD in a non-resonant way (as for not to favour a single excited state), which promotes electrons into the conduction band and holes into the valence bands (since there are typically two valence bands at the band edge, which touch at Γ). The population of excited electrons and different characteristics of holes is called an exciton complex. Exciton complexes decay into lower-occupancy exciton complexes via electron-hole recombination, which produces bright emission lines in the photoluminescence spectrum. These lines are sharp and occur at fixed frequencies corresponding to the energy level differences, and the theoretical description of their spectrum is the ultimate goal of this work.

In the Karlsson *et al.* system, the light-beam is a laser with a spot size of $1\mu\text{m}$, power in the range 25–750 nW, and wavelength of 532 nm. The semiconductor nanocrystal has a direct band-gap at Γ . The excitons with resolvable emissions have low occupancy numbers (3 or fewer of any of the three fermions—electrons, light holes, and heavy holes). Since the number of fermions excited on a single band is smaller than the number of states available on the band by many orders of magnitude (GIVE ROUGH ESTIMATE), we approximate the exciton complexes as living on Γ , i.e. each excited fermion having zero crystal momentum.

INSERT BAND STRUCTURE DIAGRAM HERE

Clearly, the phenomenon of photoluminescence and its behaviour is wholly described by the specific wavefunctions of the exciton complexes. However, finding the wavefunctions and the matrix elements of interaction operators is a near-impossible task and is not viable to make predictions about the spectrum of the quantum dot. However, we can make multiple very strong qualitative predictions (mainly regarding degeneracies of energy levels and selection rules) by using purely symmetry arguments, using the formalism of group theory. To employ group theory, we must first identify the physical symmetries of our quantum dot.

5.2.1 Envelope function method

The following approach is informed by that developed by Burt (1999), [5]. Let us consider a QD with a single excited electron which is promoted to the conduction band (the following easily generalises to holes promoted to valence bands). Disregarding the spin component of its wavefunction for simplicity, we decompose the electron's spatial wavefunction $\Psi(\vec{r})$ into plane-waves:

$$\Psi(\vec{r}) = \int d\vec{k} \tilde{\Psi}(\vec{k}) \exp\{i\vec{k} \cdot \vec{r}\} \quad (1)$$

where $\tilde{\Psi}(\vec{k})$ is the Fourier transform of $\Psi(\vec{r})$. We now decompose the integral domain into the first Brillouin zone (B.Z.) summed over the set of reciprocal lattice

vectors G :

$$\Psi(\vec{r}) = \sum_{\vec{g} \in G} \int_{\vec{k} \in 1\text{st B.Z.}} d\vec{k} \tilde{\Psi}(\vec{k} + \vec{g}) \exp\{i(\vec{k} + \vec{g}) \cdot \vec{r}\} \quad (2)$$

Note that G is equivalent to the set of wave-vectors of plane waves periodic on the Bravais lattice. Therefore, we can choose a set of basis functions $U_n(\vec{r})$ periodic on the Bravais lattice like so:

$$U_n(\vec{r}) = \sum_{\vec{g} \in G} u_n(\vec{g}) \exp\{i\vec{g} \cdot \vec{r}\} \quad (3)$$

$$U_n(\vec{r} + \vec{r}_B) = \sum_{\vec{g} \in G} u_n(\vec{g}) \exp\{i\vec{g} \cdot \vec{r}\} \exp\{i\vec{g} \cdot \vec{r}_B\} = U_n(\vec{r}) \quad (4)$$

where $\vec{r}_B \in R$ is a lattice vector and $u_n(\vec{g})$ are the coefficients of the decomposition of U_n into reciprocal lattice plane waves, typically chosen such that U_n are orthonormal. Then, inverting this decomposition, we obtain

$$\exp\{i\vec{g} \cdot \vec{r}\} = \sum_n u_n(\vec{g})^* U_n(\vec{r}) \quad (5)$$

which allows us to decompose the original wavefunction into a sum of the orthonormal basis vectors U_n and their envelope functions Υ_n :

$$\Psi(\vec{r}) = \sum_n \Upsilon_n(\vec{r}) U_n(\vec{r}) \quad (6)$$

$$\Upsilon_n(\vec{r}) = \sum_{\vec{g} \in G} \int_{\vec{k} \in \text{B.Z.}} d\vec{k} u_n(\vec{g})^* \tilde{\Psi}(\vec{k} + \vec{g}) \exp\{i\vec{k} \cdot \vec{r}\} \quad (7)$$

Now, we choose $U_n(\vec{r})$ to represent the band-edge wavestates in the bulk structure. Using a tight-binding model with spin-orbit coupling, these wavestates can be labelled by three quantum numbers: total angular momentum j , its projection onto the z -axis j_z , and the orbital energy excitation ε_n , which we assume to be in the ground state in our system due to energy occupancy statistics (as we expect the population of states other than in the ground state to be negligible for a low-power light-source). Furthermore, the quantum number j is determined by the orbital angular momentum l , which is given by the electron configuration in each specific band, and the spin $s = 1/2$ determined for electrons and electron holes by their fundamental properties.

Photonic nanostructures can, on a small scale, cease to possess a standard band-structure, instead featuring e.g. flat bands. Dresselhaus *et al.* (2007) quotes the number of Bravais lattice cells below which this occurs to be in the order of 10^2 [6, p. 213]. Our QDs have volumes typically higher than 100 nm^3 [2, p. 2], which corresponds to the number of unit cells in the order of 10^3 . Hence we can reasonably expect our system to possess a band structure. This has two consequences to our envelope function model:

1. The envelope function $\Upsilon(\vec{r})$ is varying slowly enough for it to have an approximately defined crystal momentum. As discussed in 5.2, we assume $k \approx 0$.

2. The wavefunction $\Psi(\vec{r})$ of a single excited fermion approximately corresponds to a single state on the excited band of the infinite bulk crystal band structure. In other words, there exists a basis vector U_n such that for all other basis vectors $U_m, m \neq n$, their contribution to the wavefunction is negligible.

Labelling the single contributing basis vector by the quantum numbers l, s, j, j_z , we can express the wavefunction of a single excited fermion as

$$\langle \vec{r} | \Psi \rangle = \Upsilon(\vec{r}) \langle \vec{r} | l, s = 1/2, j, j_z \rangle \quad (8)$$

As discussed in Burt (1992) [4, p. 6656], we can write down the effective Hamiltonian for the envelope function, which yields the corresponding Schrödinger equation:

$$\hat{H}_\Upsilon = -\frac{\hbar^2}{2} \nabla \cdot \frac{1}{m^*(\vec{r})} \nabla + E_0 \quad (9)$$

$$\hat{H}_\Upsilon \Upsilon(\vec{r}) = E \Upsilon(\vec{r}) \quad (10)$$

where E_0 is the band-edge energy. Now, in a parabolic Taylor expansion of the bands about Γ , we state that around the Γ point the effective mass m^* is constant. We now see that the Schrödinger equation reduces to the following form:

$$-\frac{\hbar^2}{2m^*} \nabla^2 \Upsilon = (E - E_0) \Upsilon \quad (11)$$

This is the equation of a free particle with energy $E_p = E - E_0$. Hence we can model a single excited fermion as a "particle in a box" around the Γ point for a large enough structure.

Now we consider the wavefunction of an exciton complex, which is comprised of multiple excited fermions. The interaction between the fermions is purely electromagnetic. Since the envelope functions are slowly-varying and associated to zero crystal momenta, their magnetic interaction is negligible. The magnetic interaction of the periodic basis functions gives rise to spin-orbit and orbit-orbit coupling (ignoring the hyperfine structure of spin-spin coupling), which allows us to label an exciton complex with a total angular momentum J and its projection onto the z -axis J_z as two quantum numbers. The Coulomb interaction between fermions a and b gives rise to a term in the Hamiltonian in the form

$$\hat{V}_{ab}^C(\vec{r}_a, \vec{r}_b) = \frac{q_a q_b}{4\pi\epsilon_0} \frac{1}{|\vec{r}_a - \vec{r}_b|} \quad (12)$$

This operator can be rewritten as a function of a single vector:

$$\hat{V}_{ab}^C(\vec{\xi}) = \frac{q_a q_b}{4\pi\epsilon_0} \frac{1}{\xi}, \quad \xi = |\vec{\xi}| \quad (13)$$

Note that when this operator acts on the full two-particle wavefunction:

$$\hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b) \Upsilon_a(\vec{r}_a) U_a(\vec{r}_a) \Upsilon_b(\vec{r}_b) U_b(\vec{r}_b) \quad (14)$$

the envelope functions Υ_a, Υ_b are slowly-varying, so we can state that they don't change in the volume of a single crystal lattice cell. Therefore, we can take the envelope functions outside of an integral where each vector \vec{r}_a, \vec{r}_b is confined to a single cell:

$$\int_{\vec{r}_a \in \text{cell a}} d^3 \vec{r}_a \int_{\vec{r}_b \in \text{cell b}} d^3 \vec{r}_b \hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b) \Upsilon_a(\vec{r}_a) U_a(\vec{r}_a) \Upsilon_b(\vec{r}_b) U_b(\vec{r}_b) \approx \\ \Upsilon_a(\vec{r}_a) \Upsilon_b(\vec{r}_b) \int_{\vec{r}_a \in \text{cell a}} d^3 \vec{r}_a \int_{\vec{r}_b \in \text{cell b}} d^3 \vec{r}_b \hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b) U_a(\vec{r}_a) U_b(\vec{r}_b)$$

and since U_a, U_b are periodic over the crystal lattice, we can denote $\xi = \vec{R}_{\text{cell b}} - \vec{R}_{\text{cell a}}$ to be the lattice vector equal to the displacement between the two cells, then the integral becomes

$$\int_{\vec{r}_a \in \text{cell a}} d^3 \vec{r}_a \int_{\vec{r}_b \in \text{cell b}} d^3 \vec{r}_b \hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b) \Upsilon_a(\vec{r}_a) U_a(\vec{r}_a) \Upsilon_b(\vec{r}_b) U_b(\vec{r}_b) \approx \\ \Upsilon_a(\vec{r}_a) \Upsilon_b(\vec{r}_b) \int_{\vec{r}_a \in \text{U.C.}} d^3 \vec{r}_a \int_{\vec{r}_b \in \text{U.C.}} d^3 \vec{r}_b \hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b - \xi) U_a(\vec{r}_a) U_b(\vec{r}_b)$$

where U.C. denotes a single unit cell of the crystal lattice centered around the origin (or otherwise fixed in space). Now comes the final approximation. When considering the integral of the expression 14 over an arbitrary dual volume, we partition the volumes into unit cells of the crystal lattice and then divide the integral into pairwise U.C.-U.C. integrals over a set of displacement vectors $\vec{\xi}$. For the majority of these vectors in dual volumes comparable in size to the size of the QD, the values of ξ will be larger than the dimensions of U.C. Hence we can approximate

$$\hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b - \xi) \approx \hat{V}_{ab}^C(\xi) \quad (15)$$

By denoting the set of lattice vectors in the volume V as R_V , the integral simplifies to

$$\int_V d^3 \vec{r}_a \int_V d^3 \vec{r}_b \hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b) \Upsilon_a(\vec{r}_a) U_a(\vec{r}_a) \Upsilon_b(\vec{r}_b) U_b(\vec{r}_b) \approx \\ \Pi_{ab} \sum_{\vec{r}_a \in R_V} \sum_{\vec{r}_b \in R_V} \hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b) \Upsilon_a(\vec{r}_a) \Upsilon_b(\vec{r}_b)$$

where $\Pi_{ab} = \int_{\vec{r}_a \in \text{U.C.}} d^3 \vec{r}_a \int_{\vec{r}_b \in \text{U.C.}} d^3 \vec{r}_b U_a(\vec{r}_a) U_b(\vec{r}_b)$ is a correlation constant.

Now we renormalize the correlation constant Π_{ab} using the volume of the unit cell $V_{\text{U.C.}}$, which allows us to rewrite the double sum over R_V as an integral over the dual volume:

$$\int_V d^3 \vec{r}_a \int_V d^3 \vec{r}_b \hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b) \Upsilon_a(\vec{r}_a) U_a(\vec{r}_a) \Upsilon_b(\vec{r}_b) U_b(\vec{r}_b) \approx \\ \Pi'_{ab} \int_V d^3 \vec{r}_a \int_V d^3 \vec{r}_b \hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b) \Upsilon_a(\vec{r}_a) \Upsilon_b(\vec{r}_b),$$

$$\text{where } \Pi'_{ab} = V_{\text{U.C.}}^{-2} \Pi_{ab} = \langle U_a(\vec{r}_a) U_b(\vec{r}_b) \rangle_{\text{U.C.}}$$

Since this must be true for any (sufficiently large) V , we drop the integral altogether, equating the integrands:

$$\hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b) \Psi_a(\vec{r}_a) \Psi_b(\vec{r}_b) = \Pi'_{ab} \hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b) \Upsilon_a(\vec{r}_a) \Upsilon_b(\vec{r}_b) \quad \text{on vol. avg.} \quad (16)$$

What was done here was essentially taking a volume average over the product of the basis functions $U_a U_b$, motivated by their periodicity over unit volumes much smaller than that of the quantum dot. This high-frequency periodicity manifests as a simple correlation coefficient when considering matrix elements of \hat{V}_{ab}^C .

This allows us to modify 11 to account for Coulomb interaction purely in the paradigm of envelope functions. The full effective Schrödinger equation for envelope functions (since the fine structure effects do not matter for the slowly-varying envelope functions) is then

$$\left(-\sum_i \frac{\hbar^2}{2m_i^*} \nabla_{\vec{r}_i}^2 + \sum_{i,j;i \neq j} \Pi'_{ij} \hat{V}_{ij}^C(\vec{r}_i - \vec{r}_j) \right) \Upsilon = E_{\text{exciton}} \Upsilon \quad (17)$$

where

$$\Upsilon = \prod_i \Upsilon_i(\vec{r}_i)$$

Note that the Coulomb interaction on the volumes of the scale of the unit cell of the crystal lattice is fully rotationally symmetric, and therefore will not invalidate J, J_z as good quantum numbers. However, it will affect the value of Π'_{ij} , which therefore becomes nontrivial to calculate. It will also affect the shape of the periodic functions, which we can for simplicity just denote $F_i(\vec{r}_i)$, and which have the same periodic properties as $U_i(\vec{r}_i)$, and form in totality a J, J_z eigenstate. Therefore, we expect the transformation $U_i \rightarrow F_i$ to only affect the radial dependence in the close vicinity of an atom, preserving the spherical-harmonics angular dependence in the tight-binding model.

By interpreting eq. 17, we now see that the envelope functions in an exciton complex behave as free particles in a box with added Coulomb interactions, i.e. a many-body charged particle system. Note that the potential barriers at the edges of the "box" are not infinite, and that would indeed not be a good approximation!

Note. Even though $\hat{V}_{ab}^C(\vec{r}_a - \vec{r}_b)$ diverges for $\vec{r}_a = \vec{r}_b$ (which occurs in the small subset of $R_V \otimes R_V$ where both vectors are in the same unit cell), the contribution of the integrals over these coinciding unit cells should not be disproportionately high, since when considering the volume integral in spherical coordinates centered on the asymptote, the integrand goes like $|\vec{r}_a - \vec{r}_b|$, so the integral should be approximately proportional to $V_{\text{U.C.}}^{2/3}$, and the contribution from this subset where our approximations fail to the total integral is negligible.

5.2.2 Symmetry arguments, group theory, and double groups

Now that we have decomposed the single excited fermion wavefunction into a j -eigenstate periodic in the atomic lattice and a slowly varying envelope function

which corresponds to a zero bulk-crystal momentum, we turn to symmetry arguments to make predictions about the spectrum. Indeed, finding either of the two component functions is a task beyond the scope of this work, but we can make quantitative statements about the splitting of the exciton energy levels and selection rules for transitions between these energy levels. To do this, we must consider how the exciton wavefunction transforms under symmetry transformations of the true Hamiltonian.

To review the basic applications of group theory to quantum mechanics as outlined e.g. in Dresselhaus (2002) [7], we consider the set of rotations commuting with a Hamiltonian \hat{H} . This set forms a group under multiplication (as for \hat{R}_1, \hat{R}_2 commuting with \hat{H} , $\hat{R}_1\hat{R}_2$ must be a single rotation \hat{R}_3 which also commutes with \hat{H}). This group shall be denoted as $G_{\hat{H}}$, and is referred to as the group of the Hamiltonian. As shown in standard texts, each energy level E_n of the time-independent Schrödinger eigenvalue problem $\hat{H}\Psi_n = E_n\Psi_n$ corresponds to an irreducible representation (irrep) of $G_{\hat{H}}$, which we can denote as $\Gamma_{r(n)}$, where r is some mapping. The degeneracy of E_n is then equal to the dimension of $\Gamma_{r(n)}$. Therefore, knowing the group of the Hamiltonian tells us the possible degeneracies of the energy levels and what they transform like under the symmetry transformations.

Moreover, group theory has an application to selection rules. Consider two energy levels E_a, E_b of a system with the Hamiltonian \hat{H} . If we add a perturbation \hat{H}' which allows transition between energy levels, and which transforms according to the representation $\Gamma_{\hat{H}'}$, by Fermi's golden rule the rate of transition $E_a \rightarrow E_b$ is proportional to the matrix element $\langle E_a | \hat{H}' | E_b \rangle$ (if the energy levels are degenerate, we need to pick a set of basis vectors and consider the rates of transition between each pair of basis vectors). As per [7, Ch. 7], this matrix element vanishes if the irrep direct product $\Gamma_{r(a)} \otimes \Gamma_{\hat{H}'} \otimes \Gamma_{r(b)}$ does not contain the identity representation. This allows us to decide which exciton transitions under photoluminescent electron-hole recombination will be dark in which polarisation.

Consider now the effective Hamiltonians acting on the envelope function $\Upsilon = \prod_i \Upsilon_i(\vec{r}_i)$ and the periodic function $F = \prod_i F_i(\vec{r}_i)$, respectively.

1. Υ , representing a many-body charged particle-in-a-box system, is governed in its symmetry by the shape of the box, i.e. the shape of the QD. In our system, this shape is assumed to possess C_{3v} (tetrahedral) symmetry. This symmetry shall be referred to as the *structure symmetry*.
2. F , representing a function periodic in the crystal lattice, is governed in its symmetry by the shape of the lattice, i.e. the properties of the bulk of the crystal. In our system, the crystal lattice is a zincblend structure (cubic FCC) around the [111] direction. Since the lattice has a six-fold rotation symmetry along [111], but the mirror symmetry along this axis is broken by the arrangement of the atoms, the point group symmetry in the crystal bulk is C_{6v} (INSERT FIGURE OF STRUCTURE). This symmetry shall be referred to as the *bulk symmetry*.
3. Around the individual atoms in the crystal lattice, in the tight-binding model the exciton forms a total angular momentum eigenstate $|J, J_z\rangle$. This has a full

roto-inversion symmetry, and since it is a spin-half spinor, the group describing the full roto-inversion symmetry is $SU(2) \otimes C_i$, where $C_i = \{\hat{E}, \hat{i}\}$ is the inversion group and it is isomorphic to \mathbb{Z}_2 .

Naturally, the symmetry of the true Hamiltonian will be the lowest one of these, which is in our case the structure symmetry C_{3v} —or rather, since we are discussing spin-half spinors, its double group, as will be discussed below. However, as we argue below, the bulk symmetry will be important when explaining the origin of symmetry elevation in our perturbative model.

Now, let us consider the character of the full exciton wavefunction under a symmetry transformation \hat{R} . Since the Coulomb interaction transforms according to the identity rep under roto-inversions, we can first consider the character of a single fermion wavefunction under the symmetry transformation, and then we construct the full exciton character through j -coupling, as discussed in Sec. 5.2.3. Since the single excited fermion wavefunction is a product of two functions, its character will be the product of the two constituent characters:

$$\chi^{(\Psi(\vec{r}))}(\hat{R}) = \chi^{(\Upsilon(\vec{r}))}(\hat{R}) \chi^{(U(\vec{r}))}(\hat{R}) \quad (18)$$

The character of the envelope function can be, in principle, any irrep of the structure symmetry group. However, we once again invoke the energy statistics—the population of QDs excited by a low-energy laser for which the envelope functions are out of the ground state should be negligible. Therefore, assuming the envelope function is in its ground state, we know it transforms according to the identity rep. Therefore $\chi^{(\Upsilon(\vec{r}))}(\hat{R}) = 1$.

In the tight-binding model, the band-edge eigenstate U is a convolution of the j -eigenstate which exists around each atom with the distribution of the atoms, weighted relatively to their atomic properties. Since the structure symmetry group is a subgroup of the bulk symmetry group, the bulk crystal lattice maps onto itself under every rotation in the structure symmetry, i.e. transforming according to the identity rep. Therefore the only part of the single excited fermion wavefunction which does not necessarily transform according to the identity rep is the j -eigenstate itself. The character of a j -eigenstate is just the trace of the corresponding Wigner D-matrix (CITATION), and each set of eigenstates

$$\begin{pmatrix} |j, j_z = j\rangle \\ |j, j_z = j - 1\rangle \\ \vdots \\ |j, j_z = -j\rangle \end{pmatrix} \text{ forms a basis to } \Gamma_j^{(SU(2))}$$

To extend this unto roto-inversions, we need to consider the orbital angular momentum l , which determines inversion parity. For example, in our system, the conduction band is an s -orbital, which has even parity under inversion, but the valence band is a p -orbital, which has odd parity under inversion. Determining parity specifies the irrep of the full roto-inversion group $SU(2) \otimes C_i$, which gains an index g (gerade) if even or u (ungerade) if odd under inversion.

Our approach to construct the transformation laws for the single excited fermions is therefore to consider the irreps of the full roto-inversion spinor group, and then decompose them into the true symmetry, i.e. the structure symmetry. To do this, we must construct the double group of the structure symmetry point group. Essentially, a double group encodes the spin-orbit coupling for its original group by adding the time-reversal operator as a generator. This renders rotations by 2π to result in time-reversal, and only rotations by 4π return back to the identity, in agreement with the behaviour of spin-half particles under rotation. The theory of double groups is outlined in [7, Ch. 19], and the character tables of double groups can be found in standard tables, such as [9].

Applying this approach, we find that an electron promoted to the s -orbital conduction band transforms according to $\Gamma_{j=1/2,g}$ in the full roto-inversion group, which reduces to $E_{1/2}$ in the C_{3v} double group. Conversely, a hole promoted to the p -orbital valence band transforms according to $\Gamma_{j=1/2,u} \oplus \Gamma_{j=3/2,u}$ in the full roto-inversion group. We identify $\Gamma_{j=1/2,u}$ as the split-off band which has lower energy at the band-edge, and hence will not be populated in our system. Conversely, $\Gamma_{j=3/2,u}$ decomposes into $E_{1/2} \oplus E_{3/2}$ in the C_{3v} double group, where $E_{1/2}$ corresponds to the light-hole band ($j_z = \pm 1/2$) and $E_{3/2}$ corresponds to the heavy-hole band ($j_z = \pm 3/2$). This also illustrates the symmetry-informed reason why there are two different hole types.

5.2.3 Total angular momentum coupling and Pauli's exclusion principle

here I elaborate on j and j -coupling

The band structure of our QD has the following structure:

5.3 Photoluminescence spectrum and evidence of symmetry elevation

6 Results

6.1 Treatment of parity

The theoretical treatment of parity under l and j -coupling is shown. The program ARETDoG as an implementation of this and its agreement with [1] is discussed.

6.2 Symmetry suppression theory

The first-order perturbation treatment of selection rules and its applicability to low-to-high symmetry systems is shown.

7 Discussion of results

7.1 Symmetry suppression in pyramidal quantum dots

The suppression theory in 6.2 is discussed in the context of the quantum dots grown in the mode described in 5.1. The limiting symmetry of the nanocrystalline structure is shown. The effects of strain and other causes of perturbation are discussed. The C_{3v} probing for the $X_{\bar{1},1}$ transition is discussed and explanations are offered.

7.2 Other hypothetical causes of symmetry elevation

This section serves to enumerate another effects we have identified which might cause symmetry breaking or potential elevation in QDs. These include band-mixing effects and electron gas models. Since they are not mathematically developed, my goal is to identify specifically the aspects of these hypotheses that might for a basis for a change of symmetry. I also discuss why the interplay between these effects can be neglected, as that would constitute second-order effects (and I justify this claim by qualitative arguments).

8 Conclusions

The importance of [3] on the entire research community in the context of symmetry elevation is discussed. The treatment of parity and symmetry suppression theory are described in the perspective of their generality and other areas where they may be useful are identified. The implications of the parity treatment are discussed. I conclude that [3] is a satisfactory explanation for symmetry elevation, with our symmetry suppression theory justifying the dismissal of small perturbations, e.g. by mechanical means.

9 Acknowledgements

Our supervisor, collaborators, and my friends and others for their discussion, consultation, and support.

10 Bibliography

References

- [1] Karlsson, K. F. *et al.* (2015), Spectral signatures of high-symmetry quantum dots and effects of symmetry breaking. *New Journal of Physics*, **17** 103017
- [2] Karlsson, K. F. *et al.* (2010), Fine structure of exciton complexes in high-symmetry quantum dots: Effects of symmetry breaking and symmetry elevation. *Phys. Rev. B*, **81** 161307(R)
- [3] Holsgrove, K. M. *et al.* (2022), Towards 3D characterisation of site-controlled InGaAs pyramidal QDs at the nanoscale. *J Mater Sci*, **57** 16383–16396
- [4] Burt, M. G. (1992), The justification for applying the effective-mass approximation to microstructures. *J. Phys.: Condens. Matter*, **4** 6651. doi.org/10.1088/0953-8984/4/32/003
- [5] Burt, M. G. (1999), Fundamentals of envelope function theory for electronic states and photonic modes in nanostructures. *J. Phys.: Condens. Matter*, **11** 53
- [6] Dresselhaus, M. S., Dresselhaus, G., Jorio, A. (2007), *Group Theory: Application to the Physics of Condensed Matter* (1st ed.). Springer Berlin, Heidelberg. doi.org/10.1007/978-3-540-32899-5
- [7] Dresselhaus, M. S. (2002), *Applications of Group Theory to the Physics of Solids*. Massachusetts Institute of Technology.
- [8] Biedenharn, L. C., Louck, J. D. Louck (2009), *Angular Momentum in Quantum Physics: Theory and Application (Encyclopedia of Mathematics and its Applications, Series Number 8)* (illustrated ed.). Addison-Wesley Publishing Company, Advanced Book Program. ISBN 0-201-13507-8
- [9] Altmann, S. L., Herzog, P. (1994), *Point-Group Theory Tables*. Oxford: Clarendon Press