

Volterra Battery Systems, Inc. - Cell Qualification Test Report

Document number: QR-LFP50-A-001

Document status: DRAFT - not approved

Product: VX-LFP50 Revision A

Product name: VX-LFP50 Prismatic LFP Cell

Test period: 2026-05-25 to 2026-06-03

Test site: Volterra Holland Cell Plant - Cell Test Laboratory

Test procedures: IEC 61960-3 (rated capacity), Volterra TP-CELL-004 (dimensions), TP-CELL-007 (rate capability)

Summary

Item	Result
Rated capacity (declared)	48.6 Ah
Nominal voltage	3.2 V
Rated energy	155.52 Wh
Result against internal specification	Pending approval

This report applies only to VX-LFP50 Revision A as built on the qualification lot.

1. Cell identification and dimensions

Form factor: prismatic, aluminum case

Chemistry: LFP cathode / graphite anode

Nominal voltage: 3.2 V

Charge voltage: 3.65 V

Discharge cut-off voltage: 2.5 V

Measured external dimensions: 148.0 mm x 27.0 mm x 101.0 mm

External volume: 403.60 mL

Mass (mean of samples): 905.0 g

External volume is calculated from measured external dimensions excluding terminals.

DRAFT

2. Capacity and energy

Procedure: Charge CC-CV to charge voltage at 25 C; rest 1 h; discharge at 0.2C to cut-off voltage

Sample	Discharge capacity (Ah)
S01	48.70
S02	48.50
S03	48.60
S04	48.80
S05	48.40
S06	48.60

Mean measured discharge capacity: 48.60 Ah

Declared rated capacity: 48.6 Ah

Rated energy (nominal voltage x rated capacity): 155.52 Wh

Volumetric energy density (rated energy / external volume): 385 Wh/L

DRAFT

3. Rate capability

Maximum continuous discharge current: 50 A

Maximum continuous discharge power at nominal voltage: 160 W

Capacity-to-power ratio (rated energy / max continuous power): 0.97 : 1

4. Sign-off

Test engineer: Marco Bellini, Cell Test Engineer (signed 2026-06-03)

Reviewer: _____ (pending)

Approval date: _____

DRAFT