ETH
Eidgenössische Technische Hochschule Zürich
Swiss Federal Institute of Technology Zurich

IPA



High Rate Tests of CVD Diamond Pad Detectors

RD42 Meeting

Michael Reichmann

8th May 2019

Table of Contents

Section 1

Motivation

Diamond as Detector Material

- innermost tracking layers $\rightarrow$ highest radiation damage $\mathcal{O}\left(\mathrm{GHz/cm^2}\right)$
- $\rightarrow$ **R&D towards more radiation tolerant detector designs and/or materials**

Diamond as Detector Material

- innermost tracking layers $\rightarrow$ highest radiation damage $\mathcal{O}\left(\mathrm{GHz/cm^2}\right)$
- $\rightarrow$ **R&D towards more radiation tolerant detector designs and/or materials**

Diamond as Detector Material:

- advantageous properties
- **after $1 \cdot 10^{16}\,\mathrm{n/cm^2}$ the mean drift path in diamond larger than in silicon**

Diamond as Detector Material

- innermost tracking layers → highest radiation damage $\mathcal{O}\left(\mathrm{GHz/cm^2}\right)$
- → **R&D towards more radiation tolerant detector designs and/or materials**

Diamond as Detector Material:

- advantageous properties
- **after $1 \cdot 10^{16}\,\mathrm{n/cm^2}$ the mean drift path in diamond larger than in silicon**

Work at ETH:

- investigate signals and radiation tolerance in various detector designs:
  - Pad Detectors → whole diamond as single cell readout
  - Pixel Detectors → diamond sensor on pixel readout chip
  - 3D Pixel Detectors → 3D diamond detector on pixel readout chip

Diamond as Detector Material

- innermost tracking layers → highest radiation damage $\mathcal{O}\left(\mathrm{GHz/cm^2}\right)$
- → **R&D towards more radiation tolerant detector designs and/or materials**

Diamond as Detector Material:

- advantageous properties
- **after $1 \cdot 10^{16}\,\mathrm{n/cm^2}$ the mean drift path in diamond larger than in silicon**

Work at ETH:

- investigate signals and radiation tolerance in various detector designs:
  - **Pad Detectors** → this talk
  - Pixel Detectors
  - 3D Pixel Detectors

Section 2

Website

Website

- finished analysis of all the pad data taken at PSI (Oct 2015 - Oct 2018)
- most of the following results on the website (https://diamond.ethz.ch/psi)

Section 3

Setup


SCHWEISSWERK BÜLACH AG

Test Site

- High Intensity Proton Accelerator (HIPA) at PSI (Cyclotron) $\rightarrow$ beam line PiM1
- clean positive pion beam ($\sim$98 % π^+) with momentum of 260 MeV/c
- **tunable particle fluxes from $\mathcal{O}\left(1\,\mathrm{kHz/cm^2}\right)$ to $\mathcal{O}\left(10\,\mathrm{MHz/cm^2}\right)$** with collimators
- **significant multiple scattering $\rightarrow$ worsens resolution**





Final Setup



Figure: Modular Beam Telescope

- 4 tracking planes → trigger (fast-OR) with adjustable area (max 8 mm × 7.8 mm)
- diamond pad detectors in between tracking planes
- fast scintillator → precise trigger timing of $\mathcal{O}$ (1 ns)

Setup Development



Figure: Current Setup (Aug16 - Oct18)

- scintillator → precise trigger timing of $\mathcal{O}\,(1\,\text{ns})$
- Trigger Unit (TU) → strongly simplifying setup
- global trigger → (Plane 1 AND Plane 2) AND Scintillator

Section 4

Measurements

Tested Detectors

Name	Nick	Producer	Type	T [μm]	Irr_{max}	Comments
S129	S129	e6	scCVD	528	0	reference
IIa-3	IIa-3	IIa	scCVD	?	$5 \cdot 10^{13}$	
SiD1	SiD1	PSI	Si-Diode	300	0	calibration
SiD2	SiD2	IJS	Si-Diode	100	0	calibration
2A87-e	2A87-e	II-VI	pCVD	?	$5 \cdot 10^{13}$	
II6-78	poly-A	II-VI	pCVD	?	0	
II6-79	poly-B	II-VI	pCVD	?	0	fixed surface
II6-81	poly-D	II-VI	pCVD	?	$1 \cdot 10^{14}$	
II6-94	94	II-VI	pCVD	?	0	also as pixel
II6-95	95	II-VI	pCVD	?	$5 \cdot 10^{14}$	also as pixel
II6-96	96	II-VI	pCVD	?	0	
II6-97	97	II-VI	pCVD	510	$3.5 \cdot 10^{15}$	irradiation studies
II6-B2	B2	II-VI	pCVD	455	$8 \cdot 10^{15}$	irradiation studies
II6-E5	E5	II-VI	pCVD	520	0	bcm prime test
II6-H0	H0	II-VI	pCVD	515	0	bcm prime test
II6-H8	H8	II-VI	pCVD	505	0	bcm prime test

Table: Pad Detector Information.

2015 - 2016

Diamond	May15	Aug15	Oct15	Aug16	Oct16
S129	✓(0)	✓(0)	✓(0)	✓(0)	✓(0)
IIa-3	✗	✗	✓($5 \cdot 10^{13}$)	✗	✗
SiD1	✗	✗	✗	✓(0)	✓(0)
SiD2	✗	✗	✗	✗	✓(0)
2A87-e	✗	✗	✓($5 \cdot 10^{13}$)	✗	✗
II6-78	✓(0)	✗	✗	✗	✗
II6-79	✓(0)	✓(0)	✗	✗	✗
II6-81	✓($1 \cdot 10^{14}$)	✗	✓($1 \cdot 10^{14}$)	✗	✗
II6-94	✓(0)	✗	✗	✓(0)	✗
II6-95	✓(0)	✗	✗	✓($5 \cdot 10^{14}$)	✗
II6-96	✓(0)	✗	✗	✗	✗
II6-97	✗	✓(0)	✓(0)	✓($5 \cdot 10^{14}$)	✓($1.5 \cdot 10^{15}$)
II6-B2	✗	✓(0)	✓($5 \cdot 10^{14}$)	✓($1 \cdot 10^{15}$)	✓($2 \cdot 10^{15}$)
II6-E5	✗	✗	✗	✗	✗
II6-H0	✗	✗	✗	✗	✗
II6-H8	✗	✗	✗	✗	✗

Table: Pad Detector Timeline. Irradiation in n/cm^2 in parenthesis.

2017 - 2018

Diamond	May17	Jul17	Aug17	Aug18	Oct18
S129	✓(0)	✓(0)	✓(0)	✓(0)	✗
IIa-3	✗	✗	✗	✗	✗
SiD1	✗	✗	✗	✗	✗
SiD2	✓(0)	✓(0)	✓(0)	✓(0)	✗
2A87-e	✗	✗	✗	✗	✗
II6-78	✗	✗	✗	✗	✗
II6-79	✗	✓(0)	✗	✗	✗
II6-81	✗	✗	✗	✗	✗
II6-94	✗	✗	✗	✗	✗
II6-95	✗	✗	✗	✗	✗
II6-96	✗	✗	✗	✗	✗
II6-97	✗	✓($1.5 \cdot 10^{15}$)	✓($3.5 \cdot 10^{15}$)	✗	✗
II6-B2	✗	✓($2 \cdot 10^{15}$)	✓($4 \cdot 10^{15}$)	✓($8 \cdot 10^{15}$)	✗
II6-E5	✗	✓*(0)	✗	✗	✗
II6-H0	✓*(0)	✓*(0)	✗	✗	✗
II6-H8	✗	✗	✗	✓(0)	✓*(0)

Table: Pad Detector Timeline. Irradiation in n/cm^2 in parenthesis. * - BCMPrime devices.

Scan Types

Diamond	Rate Scan	Voltage Scan	Random Scan
S129	✓	✓	✗
IIa-3	✓	✗	✗
SiD1	✓	✓	✗
SiD2	✓	✓	✗
2A87-e	✓	✗	✗
II6-78	✓	✗	✗
II6-79	✓	✗	✗
II6-81	✓	✓	✗
II6-94	✓	✓	✓
II6-95	✓	✓	✓
II6-96	✓	✗	✗
II6-97	✓	✗	✓
II6-B2	✓	✓	✓
II6-E5	✓	✗	✗
II6-H0	✓	✗	✗
II6-H8	✓	✗	✗

Table: Pad Detector Scan Types.

Section 5

Analysis

Alignment



- assume the same error for all planes: $\frac{2.5}{\sqrt{12}} \cdot$ pixel dimension
- set errors of p1 to 0 (anchor $\rightarrow$ remains untouched)
- first coarse **pre-alignment** by connecting the outer planes with a straight line
  - move inner planes by mean of the residual distribution

Alignment



- assume the same error for all planes: $\frac{2.5}{\sqrt{12}} \cdot$ pixel dimension
- set errors of p1 to 0 (anchor $\rightarrow$ remains untouched)
- first coarse **pre-alignment** by connecting the outer planes with a straight line
  - move inner planes by mean of the residual distribution
- then **fine alignment** by fitting a straight line through all planes
  - keep p1 fixed and iteratively translate and rotate the other planes according to residuals

Theoretical Distribution

Chi-squared distribution:

$$\frac{1}{2^{k/2}\Gamma\left(k/2\right)}x^{k/2-1}e^{-x/2}$$



- k = degrees of freedom
- special case of Gamma-Distribution
- theoretical distribution of the χ^2 from the track fits fully known

Distribution after Alignment





- fit function: [0]*TMath::GammaDist(x, $k/2$, 0, $\theta = 2$)
- k - number degrees of freedom = NPlanes - 2
- does not fit very well $\rightarrow$ incorrect errors of the individual points (planes)

Determination of the Errors

1. General Scaling:

- leave width of the distribution as free parameter in fit (indicator the errors)
- adjust all errors by same factor until width converges to theoretical value of 1

2. Individual Scaling:

- set one plane under test (not included in fit)
- iteratively adjust errors of the other planes





Region and Range



Region and Range



- define signal region: one bunch wide (20 ns) around the triggered signal

Region and Range



- define signal region: one bunch wide (20 ns) around the triggered signal

Region and Range



- define signal region: one bunch wide (20 ns) around the triggered signal
- find the peak within the signal region by max value

Region and Range



- define signal region: one bunch wide (20 ns) around the triggered signal
- find the peak within the signal region by max value
- signal: integrate asymmetrically around the peak (optimisation by SNR)

Region and Range



- define signal region: one bunch wide (20 ns) around the triggered signal
- find the peak within the signal region by max value
- signal: integrate asymmetrically around the peak (optimisation by SNR)
- pedestal: same integration window in centre of pre-trigger bunch

Region and Range



- define signal region: one bunch wide (20 ns) around the triggered signal
- find the peak within the signal region by max value
- signal: integrate asymmetrically around the peak (optimisation by SNR)
- pedestal: same integration window in centre of pre-trigger bunch

Integration



- integration performed on time corrected waveform
- single bin integral: (w) times the mean of the two values: $w \cdot (v1 + v2)/2$
- sum up the single integrals + interpolated edges to get the exact integration width
- normalise by the width of the integral

Section 6

Results

Tracking Resolution





- ROC = Plane
- resolution = width of the residual distribution at the plane under test
- can achieve ∼20 μm resolution at very low χ^2
- resolution at the front slightly better than in the back
  - less multiple scattering

S129



- show both mean and standard deviation of all measurement to demonstrate stability

S129



- show both mean and standard deviation of all measurement to demonstrate stability

B2

- show irradiation rate scans and drop in pulse height + snr?

97

- show irradiation rate scans and drop in pulse height + snr?

Fix Rate Dependence



(a) First measurement



(b) After reprocessing

- less than 20 % of the tested diamonds show rate dependence >10 %
- very large rate dependence at the first measurement (>90 %)
- after reprocessing and surface cleaning with RIE very stable behaviour (∼2 %)
- feasible to "fix" bad diamonds

Section 7

Conclusion

Conclusion

- empty
- moreempty
- moremoreempty

Del Fin