H2435-3K Preliminary Data Sheet

TANSOME H2435-3K is a PAN based high strength continuous carbon fiber. This fiber is ideal for demanding high strength applications such as high performance sporting goods, infrastructure, and industrial.

Typical Fiber Properties

	English		Metric	Test Method
Tensile Strength	725 Ksi		5,000 MPa	ISO 10618
Tensile Modulus	36.3 Msi		250 GPa	ISO 10618
Strain		2.00%		ISO 10618
Density	0.065 lbs/in^3		1.80 g/cm^3	ISO 10119
Yield (3K)	7,440 ft/lbs		200 g/km	ISO 1889
Sizing Content		1.0%		ISO 10548
Filament Diameter	2.8 x 10 $^{-4}$ in		7 μm	ISO 11567

Composite Properties

	English		Metric	Test Method
0° Tensile Strength	420 Ksi		2,900 MPa	ASTM D3039
0° Tensile Modulus	20.3 Msi		140 GPa	ASTM D3039
0° Tensile Strain		1.80%		ASTM D3039
0° Compressive Strength	210 Ksi		1,450 MPa	ASTM D3410
0° FlexuralStrength	246 Ksi		1,700 MPa	ASTM D790
0° Flexural Modulus	18.1 Msi		125 GPa	ASTM D790
ILSS	12.6 Ksi		87 MPa	ASTM D2344

Normalized to 60% fiber volume 120°C

* This TDS represents the preliminary physical properties of the H2435-3K sample produced this time. As H2435-3K is currently in the development stage, its specifications may be subject to change.

The above properties do not constitute any warranty or guarantees.
These values are for material selection purposes only.

Shelf Life is 2 years date of manufacturing if stored in recommended Storage condition, Refer to safety data sheet.

Hyosung Headquarters: 119, Mapo-Daero, Mapo-gu, Seoul, Korea