H2550-24K

Technical Data Sheet

TANSOME H2550-24K is a PAN based high strength continuous carbon fiber. This fiber is ideal for demanding high strength applications such as high performance sporting goods, infrastructure, and pressure vessels.

Typical Fiber Properties

	English		Metric	Test Method
Tensile Strength	800 Ksi		5,516 MPa	ISO 10618
Tensile Modulus	36.3 Msi		250 GPa	ISO 10618
Strain		2.20%		ISO 10618
Density	0.065 lbs/in^3		1.80 g/cm^3	ISO 10119
Yield (24K)	903 ft/lbs		1650 g/km	ISO 1889
Sizing Content		1.00%		ISO 10548
Filament Diameter	2.8 X 10^{-4} in		7 µm	ISO 11567

Composite Properties

	English		Metric	Test Method
0° Tensile Strength	428 Ksi		2,950 MPa	ASTM D3039
0° Tensile Modulus	20.3 Msi		140 GPa	ASTM D3039
0° Tensile Strain		2.00%		ASTM D3039
0° Compressive Strength	210 Ksi		1,450 MPa	ASTM D3410
0° Flexural Strength	261 Ksi		1,800 MPa	ASTM D790
0° Flexural Modulus	18.1 Msi		125 GPa	ASTM D790
ILSS	13.1 Ksi		90 MPa	ASTM D2344

Normalized to 60% fiber volume 120°C

The above properties do not constitute any warranty or guarantees.
These values are for material selection purposes only.

TANSOME® CARBON FIBER

Hyosung Headquarters: 119, Mapo-Daero, Mapo-gu, Seoul, Korea