Technical Data Sheet

HS HYOSUNG ADVANCED MATERIALS

H2561-28K

Standard Modulus

TANSOME H2561-28K is a PAN-based, high-strength continuous carbon fiber. This fiber is ideal for demanding, high-strength applications in next-generation pressure vessels.

Typical Fiber Properties			
Unit	US Unit	SI Unit	Test Method
Tensile Strength	885 ksi	6,100 MPa	ISO 10618
Tensile Modulus	36.3 Msi	250 GPa	ISO 10618
Tensile Strain	2.4%		ISO 10618
Density	0.065 lbs/in^3	1.80 g/cm^3	ISO 10119
Yield	958 ft/lbs	1,750 g/km	ISO 1889
Sizing Content	1.0%		ISO 10548
Filament Diameter	2.8 x 10 $^{-4}$ in	6.5 ㎛	ISO 11567

The information provided herein is based on tests conducted under controlled laboratory conditions and represents typical or average values. These values do not constitute a specification, guarantee, or warranty. Actual results may vary depending on processing conditions or when used with other materials.

Composite Properties			
Unit	English	Metric	Test Method
0° Tensile Strength	419 ksi	2,893 MPa	ASTM D3039
0° Tensile Modulus	21.5 Msi	148 GPa	ASTM D3039
0° Tensile Strain	2.00%		ASTM D3039
0° Compressive Strength	180 ksi	1,244 MPa	ASTM D3410
0° Flexural Strength	269 ksi	1,853 MPa	ASTM D790
0° Flexural Modulus	19.0 Msi	131 GPa	ASTM D790
ILSS	12.0 ksi	85 MPa	ASTM D2344

Shelf Life
36 months , Storage conditions: Temperature 10℃-35℃ (50℉-95℉); Relative humidity 50-80%

TANSOME® CARBON FIBER

Website: www.hshyosungadvancedmaterials.com I Email: tansome@hshyosung.com
119, Mapo-Daero, Mapo-Gu, Seoul, Korea 04144

Rev.30.Mar.2026