HYOSUNG ADVANCED MATERIALS CORPORATION

H3055-6K Data Sheet

TANSOME H3055-6K is a PAN based high strength intermediate modulus continuous carbon fiber. This fiber is ideal for demanding high strength applications such as high performance sporting goods, infrastructure, and pressure vessels.

Typical Fiber Properties

	English		Metric	Test Method
Tensile Strength	840 Ksi		5,800 MPa	ISO 10618
Tensile Modulus	42.1 Msi		290 GPa	ISO 10618
Strain		2.10%		ISO 10618
Density	0.064 lbs/in^3		1.78 g/cm^3	ISO 10119
Yield (6K)	4,100 ft/lbs		360 g/km	ISO 1889
Sizing Content		1.0%		ISO 10548
Filament Diameter	2.6 x 10 $^{-4}$ in		6.6 μm	ISO 11567

Composite Properties

	English		Metric	Test Method
0° Tensile Strength	450 Ksi		3,100 MPa	ASTM D3039
0° Tensile Modulus	25.4 Msi		175 GPa	ASTM D3039
0° Tensile Strain		1.80%		ASTM D3039
0° Compressive Strength	225 Ksi		1,550 MPa	ASTM D3410
0° FlexuralStrength	275 Ksi		1,900 MPa	ASTM D790
0° Flexural Modulus	21.0 Msi		145 GPa	ASTM D790
ILSS	12.8 Ksi		88 MPa	ASTM D2344

Normalized to 60% fiber volume 120°C

The above properties do not constitute any warranty or guarantees.
These values are for material selection purposes only.

Shelf Life is 2 years date of manufacturing if stored in recommended Storage condition, Refer to safety data sheet.

TANSOME® CARBON FIBER

Hyosung Headquarters: 119, Mapo-Daero, Mapo-gu, Seoul, Korea