Technical Data Sheet

HS HYOSUNG ADVANCED MATERIALS

H3065-12K

High Strength Intermediate Modulus

TANSOME H3065-12K is a PAN based ultra-high strength intermediate modulus continuous carbon fiber. This fiber is ideal for demanding high strength applications such as aerospace & defense advanced composite applications.

Typical Fiber Properties			
Unit	US Unit	SI Unit	Test Method
Tensile Strength	928 ksi	6,400 MPa	ISO 10618
Tensile Modulus	42.1 Msi	290 GPa	ISO 10618
Tensile Strain	2.2%		ISO 10618
Density	0.064 lbs/in^3	1.78 g/cm^3	ISO 10119
Yield	2,976 ft/lbs	505 g/km	ISO 1889
Sizing Content	1.0%		ISO 10548
Filament Diameter	2.0 x 10 $^{-4}$ in	5.0 ㎛	ISO 11567

The information provided herein is based on tests conducted under controlled laboratory conditions and represents typical or average values. These values do not constitute a specification, guarantee, or warranty. Actual results may vary depending on processing conditions or when used with other materials.

Composite Properties			
Unit	English	Metric	Test Method
0° Tensile Strength	494 ksi	3,400 MPa	ASTM D3039
0° Tensile Modulus	25.4 Msi	175 GPa	ASTM D3039
0° Tensile Strain	1.80%		ASTM D3039
0° Compressive Strength	232 ksi	1,600 MPa	ASTM D3410
0° Flexural Strength	283 ksi	1,950 MPa	ASTM D790
0° Flexural Modulus	21.0 Msi	145 GPa	ASTM D790
ILSS	12.8 ksi	88 MPa	ASTM D2344

Shelf Life

36 months , Storage conditions: Temperature 10℃-35℃ (50℉-95℉); Relative humidity 50-80%

TANSOME® CARBON FIBER

Website: www.hshyosungadvancedmaterials.com I Email: tansome@hshyosung.com
119, Mapo-Daero, Mapo-Gu, Seoul, Korea 04144

Rev.30.Mar.2026