SIGRAFIL® C T50-4.0/240-E100

Continuous carbon fiber tow

Material data

Properties	Units	Values
Numbers of filaments		50k
Fineness of yarn dry	tex (g/1000m)	3420
Density	g/cm³	1.80
Filament diameter	µm	7.0
Tensile strength	GPa | ksi	4.0 | 580
Tensile modulus	GPa | Msi	240 | 34.8
Elongation at break	%	1.70
Single filament resistivity	µΩm | µΩin	15 | 590
Sizing type		Epoxy
Sizing content	%	1.0
Spool weight	kg | lb	8.6 | 19
Spool length	m | ft	2500 | 8200

01 2022/0 E Printed in Germany
®registered trademarks of SGL Carbon SE

Carbon Fibers | SGL TECHNOLOGIES GmbH
Sales Europe/Middle East/Africa | cf-europe@sglcarbon.com
Sales Americas | cf-americas@sglcarbon.com
Sales Asia/Pacific | cf-asia@sglcarbon.com
www.sglcarbon.com

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our “General Conditions of Sale”.