Technical Data Sheet

HS HYOSUNG ADVANCED MATERIALS

S2450-24K

Balanced Performance

TANSOME S2450-24K is a PAN based continuous carbon fiber. Offering balanced mechanical properties, S2450 is designed for versatile applications including weaving, pultrusion, and prepreg manufacturing.

Typical Fiber Properties			
Unit	US Unit	SI Unit	Test Method
Tensile Strength	725 ksi	5,000 MPa	ISO 10618
Tensile Modulus	34.8 Msi	240 GPa	ISO 10618
Tensile Strain	2.1%		ISO 10618
Density	0.065 lbs/in^3	1.80 g/cm^3	ISO 10119
Yield	902 ft/lbs	1,650 g/km	ISO 1889
Sizing Content	1.0%		ISO 10548
Filament Diameter	2.8 x 10 $^{-4}$ in	7.0 ㎛	ISO 11567

The information provided herein is based on tests conducted under controlled laboratory conditions and represents typical or average values. These values do not constitute a specification, guarantee, or warranty. Actual results may vary depending on processing conditions or when used with other materials.

Composite Properties			
Unit	English	Metric	Test Method
0° Tensile Strength	377 ksi	2,600 MPa	ASTM D3039
0° Tensile Modulus	20.3 Msi	140 GPa	ASTM D3039
0° Tensile Strain	1.80%		ASTM D3039
0° Compressive Strength	210 ksi	1,450 MPa	ASTM D3410
0° Flexural Strength	246 ksi	1,700 MPa	ASTM D790
0° Flexural Modulus	18.1 Msi	125 GPa	ASTM D790
ILSS	12.6 ksi	87 MPa	ASTM D2344

Shelf Life
36 months , Storage conditions: Temperature 10℃-35℃ (50℉-95℉); Relative humidity 50-80%

TANSOME® CARBON FIBER

Website: www.hshyosungadvancedmaterials.com I Email: tansome@hshyosung.com
119, Mapo-Daero, Mapo-Gu, Seoul, Korea 04144

Rev.30.Mar.2026