HS HYOSUNG ADVANCED MATERIALS

S2450-48K

Balanced Performance

TANSOME S2450-48K is a PAN based continuous carbon fiber. Offering balanced mechanical properties, S2450 is designed for versatile applications including weaving, pultrusion, and prepreg manufacturing.

Typical Fiber Properties			
Unit	US Unit	SI Unit	Test Method
Tensile Strength	725 ksi	5,000 MPa	ISO 10618
Tensile Modulus	34.8 Msi	240 GPa	ISO 10618
Tensile Strain	2.1%		ISO 10618
Density	0.065 lbs/in^3	1.80 g/cm^3	ISO 10119
Yield	448 ft/lbs	3,320 g/km	ISO 1889
Sizing Content	1.0%		ISO 10548
Filament Diameter	2.8 x 10 $^{-4}$ in	7.0 ㎛	ISO 11567

The information provided herein is based on tests conducted under controlled laboratory conditions and represents typical or average values. These values do not constitute a specification, guarantee, or warranty. Actual results may vary depending on processing conditions or when used with other materials.

Shelf Life
36 months , Storage conditions: Temperature 10℃-35℃ (50℉-95℉); Relative humidity 50-80%

TANSOME® CARBON FIBER

Website: www.hshyosungadvancedmaterials.com I Email: tansome@hshyosung.com
119, Mapo-Daero, Mapo-Gu, Seoul, Korea 04144

Rev.30.Mar.2026