Technical Data Sheet

HS HYOSUNG ADVANCED MATERIALS

S2650-48K

Enhanced Modulus

TANSOME S2650-48K is a PAN based enhanced modulus continuous carbon fiber. Designed for offshore wind blade spar-cap applications, S2650-48K offers exceptional stiffness to ensure reliable performance in the growing scale of offshore wind blades.

Typical Fiber Properties			
Unit	US Unit	SI Unit	Test Method
Tensile Strength	783 ksi	5,400 MPa	ISO 10618
Tensile Modulus	37.8 Msi	260 GPa	ISO 10618
Tensile Strain	2.10%		ISO 10618
Density	0.065 lbs/in^3	1.80 g/cm^3	ISO 10119
Yield	456 ft/lbs	3,265 g/km	ISO 1889
Sizing Content	1.0%		ISO 10548
Filament Diameter	2.8 x 10 $^{-4}$ in	7.0 ㎛	ISO 11567

The information provided herein is based on tests conducted under controlled laboratory conditions and represents typical or average values. These values do not constitute a specification, guarantee, or warranty. Actual results may vary depending on processing conditions or when used with other materials.

Shelf Life

36 months , Storage conditions: Temperature 10℃-35℃ (50℉-95℉); Relative humidity 50-80%

TANSOME® CARBON FIBER

Website: www.hshyosungadvancedmaterials.com I Email: tansome@hshyosung.com
119, Mapo-Daero, Mapo-Gu, Seoul, Korea 04144

Rev.30.Mar.2026