
中国建材 | 中复神鹰

TECHNICAL DATA SHEET

# Zhongfu Shenying Carbon Fiber

# SYT55S-24K



## TECHNICAL DATA SHEET

| SYT55S-24K | Metric | | English | | Test Method | Note |
|---|---|---|---|---|---|---|
| Tensile Strength | 5880 | MPa | 852 | Ksi | GB/T 3362 | Inspection standards can be implemented according to customer requirements |
| Elastic Modulus | 295 | GPa | 42.7 | Msi | GB/T 3362 | |
| Elongation at Break | 1.9 | % | 1.9 | % | GB/T 3362 | |
| Density | 1.79 | g/cm³ | 0.064 | lbs/in³ | GB/T 30019 | |
| Linear Density | 900 | g/km | 2094 | ft/lbs | GB/T 3362 | |
| Sizing Type | Epoxy | | | | | |
| Twist | Never twisted | | | | | |


## APPLICATION FIELD

The SYT55S-24K carbon fibers applications involve aerospace, carbon/carbon composites, pressure vessel, leisure sports, Architecture & bridge, rail transit, electronic product and other fields.

## PACKAGING

The table below summarizes the standard packaging;
other bobbin sizes can be supplied to satisfy special needs.

| Filament Count | Bobbin (Net weight kg) | Bobbin Size(mm) | | | | | Spools Per case | Case (Net weight kg) |
|---|---|---|---|---|---|---|---|---|
| | | a | b | c | d | e | | |
| 24K | 4 | 76 | 82 | 280 | 160 | 250 | 6 | 24 |
| Box size： 545×355×305mm | | | | | | | | |




## STORAGE

The product should be stored in a dry, cool and ventilated warehouse, away from fire and heat sources, moisture-proof, and the stacking layer should not exceed the stacking layer limit indicated on the packaging. Under the correct storage conditions, the shelf life of the product is 2 years. After the expiration date, it can continue to be used after passing the inspection.

Notice: There is a difference in product model names between general and special application fields which shall prevail in accordance with the actual situation. the values in the table are for reference only, not guaranteed ones, technical parameters and packaging specifications are subject to change without prior notice, please consult our company for details.

**TDS Rev.2025-2: Updated January 14, 2025**